COC

Zeonex® F251R

Zeon Corporation

Position #118 · Jinsutong Reference Catalog 2026

Resin Overview

COC · Optical, Low Water Absorption. Sourced from public manufacturer technical data sheets.

This Grade

Manufacturer	Zeon Corporation
Category	COC · Optical, Low Water Absorption
Typical Use	Camera lens, optical data storage

Key Properties

Density	1.01 g/cm³
MFR (260°C/2.16 kg)	14 g/10min
Tg (DSC)	130 °C
Tensile Strength at Yield	65 MPa
Tensile Modulus	2700 MPa
Elongation at Break	3.5%
Light Transmittance (2mm)	92%
Refractive Index	1.53

Key Features

- Very low water absorption for stability
- High clarity for optical use
- Good moldability for precision parts
- RoHS compliant

Processing Conditions

Melt Temperature	280-320 °C
Mold Temperature	120-150 °C
Drying	4 h @ 100 °C
Processing Methods	Injection molding

Typical Applications

- Camera lens elements
- Optical prisms
- Optical data storage
- Precision optical instruments

Regulatory & Compliance

- USP Class VI
- RoHS compliant

> ⚠ All data sourced from public manufacturer catalogs.

Contact
Mr. Mo Hailong (莫海龙) — Business Manager · +86 138 1603 7020 · 13816037020@139.com
Shanghai Jinsutong Plastics Co., Ltd. · 1st Building, 5601 Yanqian Road, Fengxian District, Shanghai

© 2026 Shanghai Jinsutong Plastics Co., Ltd. · Jinsutong Reference Catalog 2026 · jinsutong.com/grades