EAA

SK EAA 2010

SK Yewhan

Position #110 · Jinsutong Reference Catalog 2026

Resin Overview

EAA · Asia Source, General. Sourced from public manufacturer technical data sheets.

This Grade

Manufacturer	SK Yewhan
Category	EAA · Asia Source, General
Typical Use	Asia-source alternative, foil adhesion

Key Properties

MFR (190°C/2.16 kg)	8 g/10min
Density	0.94 g/cm³
Acrylic Acid Content	8.5 wt%
Tensile Strength at Yield	19 MPa
Elongation at Break	590%
Vicat Softening Point	72 °C
Peel Strength to Aluminum	6.4 N/15mm
Cost vs DuPont	80-85%

Key Features

- Cost-competitive alternative to DuPont
- Good aluminum adhesion
- Korea/China production
- Stable supply for Asian customers

Processing Conditions

Melt Temperature	270-310 °C
Mold Temperature	N/A (extrusion)
Drying	Not required
Processing Methods	Extrusion coating, co-extrusion

Typical Applications

- Carton aluminum lamination
- Snack food packaging
- Cereal box liners
- Snack bag extrusion coating

Regulatory & Compliance

- FDA 21 CFR 177.1340
- China GB 4806.7
- RoHS compliant

> ⚠ All data sourced from public manufacturer catalogs.

Contact
Mr. Mo Hailong (莫海龙) — Business Manager · +86 138 1603 7020 · 13816037020@139.com
Shanghai Jinsutong Plastics Co., Ltd. · 1st Building, 5601 Yanqian Road, Fengxian District, Shanghai

© 2026 Shanghai Jinsutong Plastics Co., Ltd. · Jinsutong Reference Catalog 2026 · jinsutong.com/grades