EVA

Evatane® 33-400

Arkema

Position #110 · Jinsutong Reference Catalog 2026

Resin Overview

EVA · 33% VA, Adhesive. Sourced from public manufacturer technical data sheets.

This Grade

Manufacturer	Arkema
Category	EVA · 33% VA, Adhesive
Typical Use	High VA for adhesive and foam

Key Properties

MFR (190°C/2.16 kg)	40 g/10min
VA Content	33 wt%
Density	0.96 g/cm³
Melting Point (DSC)	64 °C
Vicat Softening Point	40 °C
Tensile Strength at Yield	4 MPa
Elongation at Break	850%
Hardness (Shore A)	65

Key Features

- 33% VA for high tack adhesive
- Very high MFR (40) for fast processing
- Very soft for foam
- FDA food contact compliant

Processing Conditions

Melt Temperature	160-200 °C
Mold Temperature	N/A (extrusion)
Drying	Not required
Processing Methods	Hot-melt extrusion

Typical Applications

- Hot-melt adhesive
- EVA foam with very soft feel
- Low temperature sealing
- Packaging adhesives

Regulatory & Compliance

- FDA 21 CFR 177.1350
- EU 10/2011
- RoHS compliant

> ⚠ All data sourced from public manufacturer catalogs.

Contact
Mr. Mo Hailong (莫海龙) — Business Manager · +86 138 1603 7020 · 13816037020@139.com
Shanghai Jinsutong Plastics Co., Ltd. · 1st Building, 5601 Yanqian Road, Fengxian District, Shanghai

© 2026 Shanghai Jinsutong Plastics Co., Ltd. · Jinsutong Reference Catalog 2026 · jinsutong.com/grades