EVOH

EVAL™ L100B

可乐伽

编号 #103 · 金塑通参考目录 2026

Resin Overview

EVOH · 38 mol%,高刚性. Sourced from public manufacturer technical data sheets.

This Grade

Manufacturer	可乐伽
Category	EVOH · 38 mol%,高刚性
Typical Use	高刚性障障层,结枏

Key Properties

乙烯含量	38 mol%
密度	1.17 g/cm³
流不体积率	1.3 g/10min
熔点(DSC)	172 °C
O₂ 透过率(23°C/65%RH)	0.9 cc·mil/m2·day·atm
展长涵包强度	70 MPa
展长模量	1900 MPa
断裂伸长率	220%

Key Features

- 38 mol% 高刚性
- 38 mol% 中最低 OTR
- 适合刚性障障薄膜
- FDA 和 EU 食品接触合规

Processing Conditions

流不温度	200-240 °C
模具温度	N/A (extrusion)
干燥	4 h @ 100 °C in desiccant dryer
加工方式	Co-extrusion, thermoforming

Typical Applications

- 刚性障障薄膜
- 热成型障障容器
- 高刚性包装
- 共拙包装

Regulatory & Compliance

- FDA 21 CFR 177.1360
- EU 10/2011
- RoHS 合规

> ⚠ 所有数据来源于公开厂商目录。

Contact
Mr. Mo Hailong (莫海龙) — Business Manager · +86 138 1603 7020 · 13816037020@139.com
Shanghai Jinsutong Plastics Co., Ltd. · 1st Building, 5601 Yanqian Road, Fengxian District, Shanghai

© 2026 Shanghai Jinsutong Plastics Co., Ltd. · Jinsutong Reference Catalog 2026 · jinsutong.com/grades