VECTRA® A430

Liquid Crystal Polymer

Provides many of the characteristics of A130 with added lubricity. Suitable for applications requiring excellent wear characteristics. Excellent electrical properties at high frequencies. LCP/PTFE blend. Chemical abbreviation according to ISO 1043-1 : LCP Inherently flame retardant UL-Listing V-0 in natural and black at 0.43mm thickness per UL 94 flame testing. Relative-Temperature-Index (RTI) according to UL 746B: electrical 130°C, mechanical 130°C. UL = Underwriters Laboratories (USA)

Product information

Resin Identification	(LCP-PTFE)	ISO 1043
Part Marking Code	>LCP-PTFE<	ISO 11469

Rheological properties

Molding shrinkage, parallel	0	%	ISO 294-4, 2577
Molding shrinkage, normal	0.7	%	ISO 294-4, 2577

Typical mechanical properties

Tensile modulus	1.02E6	psi	ISO 527-1/-2
Tensile stress at break, 5mm/min	21800	psi	ISO 527-1/-2
Tensile strain at break, 5mm/min	5.8	%	ISO 527-1/-2
Flexural modulus	1.03E6	psi	ISO 178
Flexural strength	17400	psi	ISO 178
Compressive modulus	870000	psi	ISO 604
Compressive stress at 1% strain	5510	psi	ISO 604
Charpy impact strength, 23°C	40.9	ftlb/in²	ISO 179/1eU
Charpy notched impact strength, 23°C	22.4	ftlb/in²	ISO 179/1eA
Izod notched impact strength, 23°C	16.2	ftlb/in²	ISO 180/1A
Izod impact strength, 23°C	31.9	ftlb/in²	ISO 180/1U
Hardness, Rockwell, M-scale	55		ISO 2039-2

Thermal properties

Melting temperature, 10°C/min	536	°F	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	329	°F	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	441	°F	ISO 75-1/-2
Temperature of deflection under load, 8 MPa	192	°F	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	280	°F	ISO 306
Coefficient of linear thermal expansion (CLTE), parallel	0.01	E-4/°F	ISO 11359-1/-2
Coefficient of linear thermal expansion (CLTE), normal	0.256	E-4/°F	ISO 11359-1/-2

Flammability

Burning Behav. at thickness h	V-0	class	IEC 60695-11-10

Electrical properties

Relative permittivity, 100Hz	3.3		IEC 62631-2-1
Relative permittivity, 1MHz	2.7		IEC 62631-2-1
Relative permittivity, 2GHz	3.46[OT, 1]		IEC 61189-2-721
Relative permittivity, 10GHz	3.12[OT]		IEC 61189-2-721
Dissipation factor, 100Hz	300	E-4	IEC 62631-2-1

VECTRA® A430

Liquid Crystal Polymer

Dissipation factor, 1MHz	160	E-4	IEC 62631-2-1
Dissipation factor, 2GHz	25[OT, 1]	E-4	IEC 61189-2-721
Dissipation factor, 10GHz	16[OT]	E-4	IEC 61189-2-721
Volume resistivity	1E13	Ohm.m	IEC 62631-3-1
Surface resistivity	1E15	Ohm	IEC 62631-3-2
Electric strength	914	kV/in	IEC 60243-1
Comparative tracking index	225		IEC 60112
Arc Resistance	130	s	UL 746B

[OT]: One time tested

[1]: Black color, tested at 1.9GHz

Injection

Drying Recommended	yes	
Drying Temperature	302	°F
Drying Time, Dehumidified Dryer	4 - 6	h
Processing Moisture Content	≤0.01	%
Melt Temperature Optimum	563	°F
Min. melt temperature	545	°F
Max. melt temperature	590	°F
Max. screw tangential speed	0.2 - 0.3	m/s
Mold Temperature Optimum	212	°F
Min. mold temperature	176	°F
Max. mold temperature	248	°F
Back pressure	435	psi
Ejection temperature	468	°F

Automotive

OEM	STANDARD
Continental	TST N 055 72.01-000

Characteristics

Processing	Injection Molding
Special characteristics	Light stabilized or stable to light, Low wear / Low friction, High Flow

Additional information

Injection molding

Preprocessing

Vectra resins are well known for their excellent thermal and hydrolytic stability. In order to ensure these properties are optimum, the resin should be dried correctly prior to processing. Vectra A-grades should be dried at 150 C for a minimum of 4 hours in a desiccant dryer.

Processing

A three-zone screw evenly divided into feed, compression, and metering zones is preferred. A higher percentage of feed flights may be needed for smaller

VECTRA® A430

Liquid Crystal Polymer

machines: 1/2 feed, 1/4 compression, 1/4 metering.

Vectra LCPs are shear thinning, their melt viscosity decreases quickly as shear rate increases. For parts that are difficult to fill, the molder can increase the injection velocity to improve melt flow.

Processing Notes

Pre-Drying

VECTRA should in principle be predried. Because of the necessary low maximum residual moisture content the use of dry air dryers is recommended. The dew point should be =< - 40° C. The time between drying and processing should be as short as possible.


Storage

For subsequent storage of the material in the dryer until processed the temperature does not need to be lowered for grades A, B, C, D and V (<= 24 h).

VECTRA® A430

Liquid Crystal Polymer


Dynamic Shear modulus-temperature



VECTRA® A430

Liquid Crystal Polymer


Stress-strain



VECTRA® A430

Liquid Crystal Polymer

Secant modulus-strain



Revised: 2026-05-22 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colorants or other additives may cause significant variations in data values. Properties of molded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.
Copyright © 2026 Celanese or its affiliates. All rights reserved.
Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates.