Celanese
The chemistry inside innovation™

VECTRA® C130

Liquid Crystal Polymer

Has the same excellent balance of properties as A130 with higher temperature capability and easier flow. Slightly more dimensional stability in vapor phase soldering than A130. Suitable for some infrared SMT applications. 30% glass reinforced. Chemical abbreviation according to ISO 1043-1 : LCP Inherently flame retardant UL-Listing V-0 in natural and black at 0.38mm thickness per UL 94 flame testing, and UL-5VA in natural at 1.5mm. Relative-Temperature-Index (RTI) according to UL 746B: electrical 240 °C, mechanical 220 °C at 0.75mm. UL = Underwriters Laboratories (USA)

Product information

Resin Identification	LCP-GF30		ISO 1043
Part Marking Code	>LCP-GF30<		ISO 11469

Rheological properties

Molding shrinkage, parallel	0.2	%	ISO 294-4, 2577
Molding shrinkage, normal	0.4	%	ISO 294-4, 2577

Typical mechanical properties

Tensile modulus	2.32E6	psi	ISO 527-1/-2
Tensile stress at break, 5mm/min	23200	psi	ISO 527-1/-2
Tensile strain at break, 5mm/min	1.6	%	ISO 527-1/-2
Flexural modulus	2.18E6	psi	ISO 178
Flexural strength	35500	psi	ISO 178
Compressive modulus	3.19E6	psi	ISO 604
Compressive stress at 1% strain	18000	psi	ISO 604
Tensile creep modulus, 1h	1.97E6	psi	ISO 899-1
Tensile creep modulus, 1000h	1.7E6	psi	ISO 899-1
Charpy notched impact strength, 23 °C	19	ftlb/in²	ISO 179/1eA
Izod notched impact strength, 23 °C	13.8	ftlb/in²	ISO 180/1A
Hardness, Rockwell, M-scale	80		ISO 2039-2

Thermal properties

Melting temperature, 10 °C/min	617	°F	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	491	°F	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	482	°F	ISO 75-1/-2
Temperature of deflection under load, 8 MPa	412	°F	ISO 75-1/-2
Vicat softening temperature, 50 °C/h 50N	378	°F	ISO 306
Coefficient of linear thermal expansion (CLTE), parallel	0.03	E-4/°F	ISO 11359-1/-2
Coefficient of linear thermal expansion (CLTE), normal	0.1	E-4/°F	ISO 11359-1/-2

Flammability

Burning Behav. at thickness h	V-0	class	IEC 60695-11-10
Oxygen index	45	%	ISO 4589-1/-2

Revised: 2025-06-26 Source: Celanese Materials Database

VECTRA® C130

Liquid Crystal Polymer

Electrical properties

Relative permittivity, 100Hz	4.2		IEC 62631-2-1
Relative permittivity, 1MHz	3.7		IEC 62631-2-1
Dissipation factor, 100Hz	140	E-4	IEC 62631-2-1
Dissipation factor, 1MHz	180	E-4	IEC 62631-2-1
Volume resistivity	1E13	Ohm.m	IEC 62631-3-1
Surface resistivity	>1E15	Ohm	IEC 62631-3-2
Electric strength	889	kV/in	IEC 60243-1
Comparative tracking index	200		IEC 60112
Arc Resistance	182	s	UL 746B

Physical/Other properties

Density	0.0581	lb/in^3	ISO 1183

Injection

Drying Recommended	yes	
Drying Temperature	302	°F
Drying Time, Dehumidified Dryer	4 - 6	h
Processing Moisture Content	≤0.01	%
Melt Temperature Optimum	626	°F
Min. melt temperature	608	°F
Max. melt temperature	644	°F
Max. screw tangential speed	0.2 - 0.3	m/s
Mold Temperature Optimum	212	°F
Min. mold temperature	176	°F
Max. mold temperature	248	°F
Back pressure	435	psi

Characteristics

Processing	Injection Molding
Special characteristics	Flame retardant, Light stabilized or stable to light, Heat stabilized or stable to heat, High Flow

Additional information

Injection molding

Preprocessing

Vectra resins are well known for their excellent thermal and hydrolytic stability. In order to ensure these properties are optimum, the resin should be dried correctly prior to processing. Vectra C-grades should be dried at 150 C for a minimum of 4 hours in a desiccant dryer.

Processing

A three-zone screw evenly divided into feed, compression, and metering zones is preferred. A higher percentage of feed flights may be needed for smaller machines: 1/2 feed, 1/4 compression, 1/4 metering.

VECTRA® C130

Liquid Crystal Polymer

Vectra LCPs are shear thinning, their melt viscosity decreases quickly as shear rate increases. For parts that are difficult to fill, the molder can increase the injection velocity to improve melt flow.

Processing Notes

Pre-Drying

VECTRA should in principle be predried. Because of the necessary low maximum residual moisture content the use of dry air dryers is recommended. The dew point should be =< - 40° C. The time between drying and processing should be as short as possible.


Storage

For subsequent storage of the material in the dryer until processed the temperature does not need to be lowered for grades A, B, C, D and V (<= 24 h).

VECTRA® C130

Liquid Crystal Polymer


Dynamic Shear modulus-temperature



VECTRA® C130

Liquid Crystal Polymer


Stress-strain



VECTRA® C130

Liquid Crystal Polymer

Secant modulus-strain



Revised: 2025-06-26 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colorants or other additives may cause significant variations in data values. Properties of molded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.
Copyright © 2026 Celanese or its affiliates. All rights reserved.
Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates.