ZENITE® 5333

Liquid Crystal Polymer

Product information

Resin Identification	LCP-MD31	ISO 1043
Part Marking Code	>LCP-MD31<	ISO 11469

Typical mechanical properties

Tensile modulus	1.35E6	psi	ISO 527-1/-2
Tensile stress at break, 50mm/min	19300	psi	ISO 527-1/-2
Tensile strain at break, 50mm/min	4.1	%	ISO 527-1/-2
Flexural modulus	1.38E6	psi	ISO 178
Flexural strength	20300	psi	ISO 178
Charpy notched impact strength, 23°C	5.47	ftlb/in²	ISO 179/1eA

Thermal properties

Melting temperature, 10°C/min	608	°F	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	500	°F	ISO 75-1/-2

Flammability

Burning Behav. at 1.5mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	0.0591	in	IEC 60695-11-10
UL recognition	yes		UL 94

Physical/Other properties

Density	0.0585	lb/in³	ISO 1183

Injection

Drying Recommended	yes	
Drying Temperature	302	°F
Drying Time, Dehumidified Dryer	4 - 6	h
Processing Moisture Content	≤0.01	%
Melt Temperature Optimum	653	°F
Min. melt temperature	644	°F
Max. melt temperature	662	°F
Max. screw tangential speed	0.2 - 0.3	m/s
Mold Temperature Optimum	212	°F
Min. mold temperature	176	°F
Max. mold temperature	248	°F

Characteristics

Processing	Injection Molding
Special characteristics	Flame retardant, Heat stabilized or stable to heat, High Flow, Lead-free soldering resistant

ZENITE® 5333

Liquid Crystal Polymer

Additional information

Processing Notes

Pre-Drying


Please allow time for resin to reach drying temperature. Insure filter element is clean and there is sufficient air flow (>1 ft/sec. space velocity) across surface of pellets Extended drying at 300 °F (150 °C) up to 24 hours will not harm resin. Hopper dryers with dual desiccant cartridges (one active while the other is regenerating) are highly recommended.

Drying Conditions using Dehumidified Hopper Dryer *Dew point of dried air should be -40 °F (-40 °C) or below*
Minimum Drying Time at Temperature
6 hr

ZENITE® 5333

Liquid Crystal Polymer

Stress-strain




Revised: 2025-03-20 Source: Celanese Materials Database

ZENITE® 5333

Liquid Crystal Polymer

Secant modulus-strain



Revised: 2025-03-20 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colorants or other additives may cause significant variations in data values. Properties of molded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.
Copyright © 2026 Celanese or its affiliates. All rights reserved.
Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates.