LCP

Vectra® V150XL

Ticona (Celanese)

Position #114 · Jinsutong Reference Catalog 2026

Resin Overview

LCP · Medium Viscosity, 30% Glass. Sourced from public manufacturer technical data sheets.

This Grade

Manufacturer	Ticona (Celanese)
Category	LCP · Medium Viscosity, 30% Glass
Typical Use	High-stiffness SMT connectors, structural

Key Properties

Density	1.65 g/cm³
Tensile Strength at Break	180 MPa
Tensile Modulus	15000 MPa
Elongation at Break	1.8%
HDT (1.8 MPa)	275 °C
Dk (1 GHz)	3.4
Df (1 GHz)	0.016
UL 94 Rating	V-0 @ 0.75mm

Key Features

- Medium viscosity grade
- 30% glass fiber for high stiffness
- Lead-free reflow compatible
- UL 94 V-0 flame retardant

Processing Conditions

Melt Temperature	300-330 °C
Mold Temperature	80-130 °C
Drying	4 h @ 150 °C in desiccant dryer
Processing Methods	Injection molding

Typical Applications

- High-density SMT connectors
- Camera module components
- BGA socket housings
- Industrial connectors

Regulatory & Compliance

- UL 94 V-0 listed
- RoHS compliant

> ⚠ All data sourced from public manufacturer catalogs.

Contact
Mr. Mo Hailong (莫海龙) — Business Manager · +86 138 1603 7020 · 13816037020@139.com
Shanghai Jinsutong Plastics Co., Ltd. · 1st Building, 5601 Yanqian Road, Fengxian District, Shanghai

© 2026 Shanghai Jinsutong Plastics Co., Ltd. · Jinsutong Reference Catalog 2026 · jinsutong.com/grades