PA46

Stanyl® TE200F6

DSM (now Envalior)

Position #113 · Jinsutong Reference Catalog 2026

Resin Overview

PA46 · 30% Glass, General. Sourced from public manufacturer technical data sheets.

This Grade

Manufacturer	DSM (now Envalior)
Category	PA46 · 30% Glass, General
Typical Use	High-temp automotive, connectors

Key Properties

Density	1.41 g/cm³
MVR (275°C/5 kg)	12 cm³/10min
Melting Point (DSC)	295 °C
Tensile Strength at Break	175 MPa
Tensile Modulus	10000 MPa
Elongation at Break	2.5%
HDT (1.8 MPa)	280 °C
Continuous Use Temperature	170 °C

Key Features

- 30% glass fiber for high stiffness
- High heat 170°C continuous
- Good for SMT reflow processing
- Wide processing window

Processing Conditions

Melt Temperature	290-320 °C
Mold Temperature	80-120 °C
Drying	4 h @ 80 °C in desiccant dryer
Processing Methods	Injection molding

Typical Applications

- High-temp automotive connectors
- SMT power components
- Industrial electronics
- High-current electrical

Regulatory & Compliance

- RoHS compliant
- REACH registered

> ⚠ All data sourced from public manufacturer catalogs.

Contact
Mr. Mo Hailong (莫海龙) — Business Manager · +86 138 1603 7020 · 13816037020@139.com
Shanghai Jinsutong Plastics Co., Ltd. · 1st Building, 5601 Yanqian Road, Fengxian District, Shanghai

© 2026 Shanghai Jinsutong Plastics Co., Ltd. · Jinsutong Reference Catalog 2026 · jinsutong.com/grades