PA46

Stanyl® TW241B3

DSM (now Envalior)

Position #111 · Jinsutong Reference Catalog 2026

Resin Overview

PA46 · 30% Glass, Black, Heat Stable. Sourced from public manufacturer technical data sheets.

This Grade

Manufacturer	DSM (now Envalior)
Category	PA46 · 30% Glass, Black, Heat Stable
Typical Use	High-temp automotive, SMT connectors

Key Properties

Density	1.41 g/cm³
MVR (275°C/5 kg)	10 cm³/10min
Melting Point (DSC)	295 °C
Tensile Strength at Break	170 MPa
Tensile Modulus	10000 MPa
Elongation at Break	2.5%
HDT (1.8 MPa)	285 °C
Color	Black

Key Features

- 30% glass fiber for high stiffness
- Heat stabilized for sustained use
- Black pre-compounded
- Suitable for SMT reflow processing

Processing Conditions

Melt Temperature	290-320 °C
Mold Temperature	80-120 °C
Drying	4 h @ 80 °C in desiccant dryer
Processing Methods	Injection molding

Typical Applications

- High-temp SMT connectors
- Automotive under-hood
- Power tool housings
- EV power electronics

Regulatory & Compliance

- RoHS compliant
- REACH registered

> ⚠ All data sourced from public manufacturer catalogs.

Contact
Mr. Mo Hailong (莫海龙) — Business Manager · +86 138 1603 7020 · 13816037020@139.com
Shanghai Jinsutong Plastics Co., Ltd. · 1st Building, 5601 Yanqian Road, Fengxian District, Shanghai

© 2026 Shanghai Jinsutong Plastics Co., Ltd. · Jinsutong Reference Catalog 2026 · jinsutong.com/grades