Zytel® 101F NC010

NYLON RESIN

Common features of Zytel® nylon resin include mechanical and physical properties such as high mechanical strength, excellent balance of stiffness and toughness, good high temperature performance, good electrical and flammability properties, good abrasion and chemical resistance. In addition, Zytel® nylon resins are available in different modified and reinforced grades to create a wide range of products with tailored properties for specific processes and end-uses. Zytel® nylon resin, including most flame retardant grades, offer the ability to be coloured.

The good melt stability of Zytel® nylon resin normally enables the recycling of properly handled production waste. If recycling is not possible, we recommend, as the preferred option, incineration with energy recovery (-31kJ/g of base polymer) in appropriately equipped installations. For disposal, local regulations have to be observed.

Zytel® nylon resin typically is used in demanding applications in the automotive, furniture, domestic appliances, sporting goods and construction industry.

Zytel® 101F NC010 is an internally lubricated polyamide 66 resin for injection molding. It was developed for fast cycles and high productivity.

Product information

Resin Identification	PA66	ISO 1043
Part Marking Code	>PA66<	ISO 11469
ISO designation	ISO 16396-PA66,,M1G1NR,S14-030	
Infrared spectrum	available	

Rheological properties

	dry/cond.		
Viscosity number	4150 / *	in³/lb	ISO 307, 1628
Molding shrinkage, parallel	1.4 / -	%	ISO 294-4, 2577
Molding shrinkage, normal	1.4 / -	%	ISO 294-4, 2577
Postmolding shrinkage, normal, 48h at 80 °C	0.1 / *	%	ISO 294-4
Postmolding shrinkage, parallel, 48h at 80 °C	0.2 / *	%	ISO 294-4

Typical mechanical properties

	dry/cond.		
Tensile modulus	450000 / 203000	psi	ISO 527-1/-2
Tensile stress at yield, 50mm/min	12000 / 8000	psi	ISO 527-1/-2
Tensile strain at yield, 50mm/min	4.5 / 25	%	ISO 527-1/-2
Nominal strain at break	20 / >50	%	ISO 527-1/-2
Tensile strain at break, 50mm/min	40 / -	%	ISO 527-1/-2
Flexural modulus	406000 / 174000	psi	ISO 178
Flexural strength	16700 / 10900	psi	ISO 178
Tensile creep modulus, 1h	* / 203000	psi	ISO 899-1
Tensile creep modulus, 1000h	* / 135000	psi	ISO 899-1
Charpy impact strength, 23 °C	N / N	ftlb/in²	ISO 179/1eU
Charpy impact strength, -30 °C	190 / N	ftlb/in²	ISO 179/1eU
Charpy notched impact strength, 23 °C	2.85 / 6.18	ftlb/in²	ISO 179/1eA
Charpy notched impact strength, -30 °C	2.14 / 1.43	ftlb/in²	ISO 179/1eA
Izod notched impact strength, 23 °C	2.62 / 5.23	ftlb/in²	ISO 180/1A
Izod notched impact strength, -30 °C	2.85 / 1.9	ftlb/in²	ISO 180/1A
Izod notched impact strength, -40 °C	2.62 / 1.43[A]	ftlb/in²	ISO 180/1A
Izod impact strength, 23 °C	143 / N	ftlb/in²	ISO 180/1U

Zytel® 101F NC010

NYLON RESIN

Izod impact strength, -30 °C	143 / N[A]	ftlb/in²	ISO 180/1U
Hardness, Rockwell, R-scale	121 / 108		ISO 2039-2

[A]: Assessed

Thermal properties

	dry/cond.		
Melting temperature, 10 °C/min	504 / *	°F	ISO 11357-1/-3
Glass transition temperature, 10 °C/min	158 / 104	°F	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	158 / *	°F	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	374 / *	°F	ISO 75-1/-2
Vicat softening temperature, 50 °C/h 50N	464 / *	°F	ISO 306
Ball pressure test	464 / -	°F	IEC 60695-10-2
Coefficient of linear thermal expansion (CLTE), parallel	0.56 / *	E-4/°F	ISO 11359-1/-2
Coefficient of linear thermal expansion (CLTE), normal	0.611 / *	E-4/°F	ISO 11359-1/-2
Thermal conductivity of melt	0.16	W/(m K)	ISO 22007-2
Effective thermal diffusivity, flow	5E-8	m²/s	ISO 22007-4
Specific heat capacity of melt	2790	J/(kg K)	ISO 22007-4
RTI, electrical, 0.75mm	266	°F	UL 746B
RTI, electrical, 1.5mm	266	°F	UL 746B
RTI, electrical, 3.0mm	266	°F	UL 746B
RTI, electrical, 6mm	266	°F	UL 746B
RTI, impact, 0.75mm	167	°F	UL 746B
RTI, impact, 1.5mm	167	°F	UL 746B
RTI, impact, 3.0mm	167	°F	UL 746B
RTI, impact, 6mm	167	°F	UL 746B
RTI, strength, 0.75mm	185	°F	UL 746B
RTI, strength, 1.5mm	185 / *	°F	UL 746B
RTI, strength, 3.0mm	185	°F	UL 746B
RTI, strength, 6mm	185	°F	UL 746B

Flammability

	dry/cond.		
Burning Behav. at 1.5mm nom. thickn.	V-2 / *	class	IEC 60695-11-10
Thickness tested	0.0591 / *	in	IEC 60695-11-10
UL recognition	yes / *		UL 94
Burning Behav. at thickness h	V-2 / *	class	IEC 60695-11-10
Thickness tested	0.0280 / *	in	IEC 60695-11-10
UL recognition	yes / *		UL 94
Oxygen index	28 / *	%	ISO 4589-1/-2
Glow Wire Flammability Index, 0.75mm	1760 / -	°F	IEC 60695-2-12
Glow Wire Flammability Index, 1.5mm	1760 / -	°F	IEC 60695-2-12
Glow Wire Flammability Index, 3.0mm	1760 / -	°F	IEC 60695-2-12
Glow Wire Ignition Temperature, 0.75mm	1340 / -	°F	IEC 60695-2-13
Glow Wire Ignition Temperature, 1.5mm	1380 / -	°F	IEC 60695-2-13
Glow Wire Ignition Temperature, 3.0mm	1470 / -	°F	IEC 60695-2-13
Glow Wire Temperature, No Flame, 1mm	1380 / -	°F	IEC 60335-1
Glow Wire Temperature, No Flame, 2mm	1340 / -	°F	IEC 60335-1
FMVSS Class	SE		ISO 3795 (FMVSS 302)
Burning rate, Thickness 1 mm		in/min	ISO 3795 (FMVSS 302)

Zytel® 101F NC010

NYLON RESIN

Electrical properties

	dry/cond.		
Relative permittivity, 100Hz	3.8 / 8		IEC 62631-2-1
Relative permittivity, 1MHz	3.6 / 4.6		IEC 62631-2-1
Dissipation factor, 100Hz	140 / -	E-4	IEC 62631-2-1
Dissipation factor, 1MHz	180 / 1000	E-4	IEC 62631-2-1
Volume resistivity	1E13 / 1E10	Ohm.m	IEC 62631-3-1
Electric strength	800 / 660	kV/in	IEC 60243-1
Comparative tracking index	600 / -		IEC 60112
Comparative tracking index, 23 °C	0 / -	PLC	UL 746A

Physical/Other properties

	dry/cond.		
Humidity absorption, 2mm	2.6 / *	%	Sim. to ISO 62
Water absorption, 2mm	8.5 / *	%	Sim. to ISO 62
Density	0.0412 / -	lb/in³	ISO 1183
Density of melt	60.6	lb/ft³	

Film properties

	dry/cond.		
Strain at yield, parallel	4.5 / *	%	ISO 527-3

Emissions

	dry/cond.		
Emission of organic compounds	6.5	µgC/g	VDA 277
Odor test	3	class	VDA 270
Fogging, G-value (condensate)	0.1 / *	mg	ISO 6452

Injection

Drying Recommended	yes	
Drying Temperature	176	°F
Drying Time, Dehumidified Dryer	2 - 4	h
Processing Moisture Content	≤0.2	%
Melt Temperature Optimum	563	°F
Min. melt temperature	536	°F
Max. melt temperature	581	°F
Max. screw tangential speed	≤0.4	m/s
Mold Temperature Optimum	158	°F
Min. mold temperature	104	°F
Max. mold temperature	203	°F
Hold pressure range	7250 - 14500	psi
Hold pressure time	0.102	s/mil
Hold Pressure Time (h is the max. wall thickness of the part in mm)	h^2+2	s
Ejection temperature	374	°F

Zytel® 101F NC010

NYLON RESIN

Automotive

OEM	STANDARD	ADDITIONAL INFORMATION
BMW	GS93016-PA66	
Mercedes-Benz	DBL5410.00 PA66	
Stellantis	B62 0300 / 61/212E/210M	CPN1938, CPN2012;01378_23_01240;1/212E/210M
Stellantis - Chrysler	MS.50017 / CPN-1938	Natural
Stellantis - Chrysler	MS.50017 / CPN-2012	Natural
VW Group	VW 50127 PA66-1	
VW Group	VW 50133 PA66-1-A	


Characteristics

Processing	Injection Molding
Additives	Release agent
Special characteristics	Fast Production Cycle

Zytel® 101F NC010

NYLON RESIN


Dynamic Shear modulus-temperature (cond.)



Zytel® 101F NC010

NYLON RESIN


Dynamic Tensile modulus-temperature (dry)



Zytel® 101F NC010

NYLON RESIN

Dynamic Tensile modulus-temperature (cond.)




Revised: 2026-08-12 Source: Celanese Materials Database

Zytel® 101F NC010

NYLON RESIN


Stress-strain (dry)



Zytel® 101F NC010

NYLON RESIN


Stress-strain (cond.)



Zytel® 101F NC010

NYLON RESIN

Secant modulus-strain (dry)




Revised: 2026-08-12 Source: Celanese Materials Database

Zytel® 101F NC010

NYLON RESIN

Secant modulus-strain (cond.)



Zytel® 101F NC010

NYLON RESIN

Chemical Media Resistance

Acids

- ✔ Acetic Acid (5% by mass), 23°C
- ✔ Citric Acid solution (10% by mass), 23°C
- ✔ Lactic Acid (10% by mass), 23°C
- ✘ Hydrochloric Acid (36% by mass), 23°C
- ✘ Nitric Acid (40% by mass), 23°C
- ✘ Sulfuric Acid (38% by mass), 23°C
- ✘ Sulfuric Acid (5% by mass), 23°C
- ✘ Chromic Acid solution (40% by mass), 23°C

Bases

- ✘ Sodium Hydroxide solution (35% by mass), 23°C
- ✔ Sodium Hydroxide solution (1% by mass), 23°C
- ✔ Ammonium Hydroxide solution (10% by mass), 23°C

Alcohols

- ✔ Isopropyl alcohol, 23°C
- ✔ Methanol, 23°C
- ✔ Ethanol, 23°C

Hydrocarbons

- ✔ n-Hexane, 23°C
- ✔ Toluene, 23°C
- ✔ iso-Octane, 23°C

Ketones

- ✔ Acetone, 23°C

Ethers

- ✔ Diethyl ether, 23°C

Mineral oils

- ✔ SAE 10W40 multigrade motor oil, 23°C
- ✘ SAE 10W40 multigrade motor oil, 130°C
- ✘ SAE 80/90 hypoid-gear oil, 130°C
- ✔ Insulating Oil, 23°C
- ✘ Motor oil OS206 304 Ref.Eng.Oil, ISP, 135°C
- ✘ Automatic hypoid-gear oil Shell Donax TX, 135°C
- ✘ Hydraulic oil Pentosin CHF 202, 125°C

Standard Fuels

- ✔ ISO 1817 Liquid 1 - E5, 60°C
- ✔ ISO 1817 Liquid 2 - M15E4, 60°C
- ✔ ISO 1817 Liquid 3 - M3E7, 60°C
- ✔ ISO 1817 Liquid 4 - M15, 60°C
- ✔ Standard fuel without alcohol (pref. ISO 1817 Liquid C), 23°C
- ✔ Standard fuel with alcohol (pref. ISO 1817 Liquid 4), 23°C
- ✔ Diesel fuel (pref. ISO 1817 Liquid F), 23°C
- ✔ Diesel fuel (pref. ISO 1817 Liquid F), 90°C
- ✘ Diesel fuel (pref. ISO 1817 Liquid F), >90°C

Zytel® 101F NC010

NYLON RESIN

Salt solutions

- ✔ Sodium Chloride solution (10% by mass), 23°C
- ✘ Sodium Hypochlorite solution (10% by mass), 23°C
- ✔ Sodium Carbonate solution (20% by mass), 23°C
- ✔ Sodium Carbonate solution (2% by mass), 23°C
- ✘ Zinc Chloride solution (50% by mass), 23°C

Other

- ✔ Ethyl Acetate, 23°C
- ✘ Hydrogen peroxide, 23°C
- ✘ DOT No. 4 Brake fluid, 130°C
- ✘ Ethylene Glycol (50% by mass) in water, 108°C
- ✔ 1% nonylphenoxy-polyethyleneoxy ethanol in water, 23°C
- ✔ 50% Oleic acid + 50% Olive Oil, 23°C
- ✔ Water, 23°C
- ✘ Water, 90°C
- ✘ Phenol solution (5% by mass), 23°C

Symbols used:

✔ possibly resistant
Defined as: Supplier has sufficient indication that contact with chemical can be potentially accepted under the intended use conditions and expected service life. Criteria for assessment have to be indicated (e.g. surface aspect, volume change, property change).

✘ not recommended - see explanation
Defined as: Not recommended for general use. However, short-term exposure under certain restricted conditions could be acceptable (e.g. fast cleaning with thorough rinsing, spills, wiping, vapor exposure).

Revised: 2026-08-12 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colorants or other additives may cause significant variations in data values. Properties of molded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.
Copyright © 2026 Celanese or its affiliates. All rights reserved.
Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates.