Celanese
The chemistry inside innovation™

Zytel® 74G50ARX ECO-R 311 BLK1

NYLON RESIN

Zytel® 74G50ARX ECO-R 311 BLK1 incorporates 30% of post-industrial recycled content by weight in the finished product. It is a 50% Glass Reinforced, Heat Stabilized, Polyamide 66 designed for Automotive industry.

产品信息

树脂鉴别	(PA66+PA6)-GF50 (REC30)		ISO 1043
制品标识码	>(PA66+PA6)-GF50 (REC30)<		ISO 11469
连续使用温度	130	°C	IEC 60216-1

流变性能

模塑收缩率范围, 平行	0.1 - 0.5	%	ISO 294-4, 2577
模塑收缩率范围, 垂直	0.5 - 0.9	%	ISO 294-4, 2577

机械性能

	dry/cond.		
拉伸模量	16300 / 12000	MPa	ISO 527-1/-2
拉伸断裂应力, 5mm/min	200 / 140	MPa	ISO 527-1/-2
断裂伸长率, 5mm/min	2.3 / 3.3	%	ISO 527-1/-2
弯曲模量	14500 / -	MPa	ISO 178
弯曲强度	300 / -	MPa	ISO 178
简支梁无缺口冲击强度, 23°C	75 / 80	kJ/m²	ISO 179/1eU
简支梁无缺口冲击强度, -30°C	45 / -	kJ/m²	ISO 179/1eU
简支梁缺口冲击强度, 23°C	14 / 16	kJ/m²	ISO 179/1eA
简支梁缺口冲击强度, -30°C	8.5 / -	kJ/m²	ISO 179/1eA
球压痕硬度, H 961/30	230 / -	MPa	ISO 2039-1

热性能

	dry/cond.		
熔融温度, 10°C/min	260 / *	°C	ISO 11357-1/-3
热变形温度, 1.8 MPa	235 / *	°C	ISO 75-1/-2
热变形温度, 0.45 MPa	250 / *	°C	ISO 75-1/-2
线性热膨胀系数, 平行	20 / *	E-6/K	ISO 11359-1/-2
线性热膨胀系数, 垂直	80 / *	E-6/K	ISO 11359-1/-2

其它性能

	dry/cond.		
吸湿率, 2mm	1.2 / *	%	类似ISO 62
吸水率, 2mm	4.1 / *	%	类似ISO 62
密度	1560 / -	kg/m³	ISO 1183

注塑

建议干燥	是	
干燥温度	80	°C
干燥时间，除湿干燥机	2 - 4	h
加工前水分含量	≤ 0.15	%
最优熔体温度	285	°C
最低熔体温度***	275	°C
最高熔体温度	295	°C
螺杆最大切线速度	≤ 0.2	m/s

Revised: 2025-07-08 Source: Celanese Materials Database

Zytel® 74G50ARX ECO-R 311 BLK1

NYLON RESIN

最优模具温度	100 °C
最低模具温度	70 °C
最高模具温度	120 °C

特性

加工方法	注塑
特殊性能	热稳定
可持续	含有可回收成分

其他信息

注塑

Preprocessing

PA materials, stocked in a moisture-proof packaging, can be processed without drying; however, it is always recommended drying the product that comes from a large package (e.g. Octabin). The moisture content suggested for the injection molding process should be lower than 0.15%, according to the grade and to the molded part characteristics. The materials containing flame retardants should have moisture content below 0.10%. Red phosphorous containing grades must always be dried below 0.08%. The drying time depends on the moisture content and the drying conditions. Typically, 4-8 hours at 80-90°C using dehumidified air (dew point of -20°C) are suitable conditions for a starting moisture content of 0.20%-0.40%.

Processing

The following conditions apply to a standard injection molding process. Machine temperatures: barrel 265-290°C (PA66), 235-270°C (PA6), nozzle and hot runners up to 300°C (up to 290°C products with flame retardants). Mold temperatures: 60-80°C, (80-100°C highly reinforced grades). Back pressure: typically, 5-10 bar (hydraulic pressure). Temperatures exceeding 300°C and long residence time could lead to additives degradation and brittleness of the material. In case of gas generation in the melt, please verify moisture content and processing temperatures. Usage of regrind is possible depending on the molded part characteristics. For further details, please refer to the document 'Instructions for injection molding' or contact our technical support team.

Postprocessing

PA materials reach their final performance with a water content of about 1.5 to 3.5% by weight, depending on the type. This percentage corresponds to the point of equilibrium between the rates of absorption and desorption of moisture. After molding, in favorable environmental conditions, a part can quickly absorbs moisture up to 0.5-1.0%, while the equilibrium will be reached during its life. A conditioning treatment can accelerate further the initial water absorption of the molded parts. Conditioning is usually carried out in hot and humid environment (for example 50°C, 100% RH), inside climatic chambers. Slight dimensional variations (increase in volume due to the water absorbed) must be considered, especially in unfilled grades. Post-treatments of parts may also include the


Zytel® 74G50ARX ECO-R 311 BLK1

NYLON RESIN

annealing (60-80 °C in oven, up to four hours). This procedure can be useful to relax any internal stresses.

51016039.21023756.21023755


应力 - 应变 (dry)



Zytel® 74G50ARX ECO-R 311 BLK1

NYLON RESIN


应力 - 应变 (cond.)



Zytel® 74G50ARX ECO-R 311 BLK1

NYLON RESIN

正割模量 - 应变 (dry)




Revised: 2025-07-08 Source: Celanese Materials Database

Zytel® 74G50ARX ECO-R 311 BLK1

NYLON RESIN

正割模量 - 应变 (cond.)



Revised: 2025-07-08 Source: Celanese Materials Database

用户须知： 所示数值基于实验室试样测试，代表本色材料标准属性范围内的数据。这些数值本身并不能作为任何部件设计的充分依据，且不旨在用于确定最大值、最小值或规格值范围。着色剂或其他添加剂可能会导致数据值的显著变化。模塑部件的性能会受到多种因素的影响，包括但不限于材料选择、添加剂、部件设计、加工条件和环境暴露。除了那些明确标识为医用级的产品（包括 MT® 产品标识或其他标识），塞拉尼斯的产品不旨在用于医疗或牙科植入。无论产品名称如何，确定特定材料和部件设计是否适用于用户所拟的任何用途以及使用方式是用户自身的责任，用户必须保证后续加工的材料满足其特定产品或用途的需要。据我们所知，本出版物中包含的信息是准确的；但是，我们对此处信息的准确性和完整性不承担任何责任。本出版物中包含的信息不应被视为对我们产品特定性能的承诺或保证。用户应自行负责调查使用本出版物中提及的材料是否侵犯了任何现有专利。此外，考虑到可能产生的不良影响，有必要将人类与许多材料的接触降至最低实际限度。对于本出版物中提到的任何危害，我们既不建议也不保证这些危害是唯一存在的危害。我们建议，打算依赖本出版物中的任何建议或使用本出版物中提及的任何设备、加工技术或材料的人，应确信他们能够满足所有适用的安全和健康标准。我们强烈建议用户在处理每种材料时，都要寻求并遵守制造商的最新说明，并且只委托受过适当培训的人员来处理这些材料。请拨打所列电话号码，了解更多技术信息。在尝试处理我们的产品之前，请致电客户服务部索取相应的材料安全数据表 (MSDS)。
(Copyright) 2026 塞拉尼斯或其附属公司。保留所有权利。
除非另有说明，Celanese®、注册的 C-ball 设计和本文中标有 ®、TM、SM 的所有其他商标均为 Celanese 或其附属公司的商标。