Zytel® 80G30ARX ECO-R 311 BLK1 (DEVELOPMENTAL)

NYLON RESIN

Zytel® 80G30ARX ECO-R 311 BLK1 incorporates 30% of post-industrial recycled content by weight in the finished product. It is a 30% Glass Reinforced, Impact Modified, Polyamide 66 suitable for a broad field of applications.

产品信息

树脂鉴别	PA66-I-GF30 (REC30)	ISO 1043
制品标识码	>PA66-I-GF30 (REC30)<	ISO 11469
连续使用温度	130 °C	IEC 60216-1

流变性能

模塑收缩率范围, 平行	0.2 - 0.5 %	ISO 294-4, 2577
模塑收缩率范围, 垂直	0.5 - 0.9 %	ISO 294-4, 2577

机械性能

	dry/cond.		
拉伸模量	7300/-	MPa	ISO 527-1/-2
拉伸断裂应力, 5mm/min	105/-	MPa	ISO 527-1/-2
断裂伸长率, 5mm/min	3.8/-	%	ISO 527-1/-2
简支梁无缺口冲击强度, 23°C	70/-	kJ/m²	ISO 179/1eU
简支梁缺口冲击强度, 23°C	14/-	kJ/m²	ISO 179/1eA

热性能

	dry/cond.		
熔融温度, 10°C/min	260/*	°C	ISO 11357-1/-3

阻燃性能

	dry/cond.		
1.5mm名义厚度时的阻燃性	HB/*	class	IEC 60695-11-10

其它性能

	dry/cond.		
吸湿率, 2mm	1.3/*	%	类似ISO 62
吸水率, 2mm	4.7/*	%	类似ISO 62
密度	1300/-	kg/m³	ISO 1183

注塑

建议干燥	是	
干燥温度	80	°C
干燥时间，除湿干燥机	2 - 4	h
加工前水分含量	≤ 0.15	%
最优熔体温度	285	°C
最低熔体温度***	275	°C
最高熔体温度	295	°C
螺杆最大切线速度	≤ 0.2	m/s
最优模具温度	100	°C
最低模具温度	70	°C
最高模具温度	120	°C

Revised: 2025-07-08 Source: Celanese Materials Database

Zytel® 80G30ARX ECO-R 311 BLK1 (DEVELOPMENTAL)

NYLON RESIN

特性

加工方法	注塑
特殊性能	抗冲改性, 热稳定
可持续	含有可回收成分

其他信息

注塑

Preprocessing

PA materials, stocked in a moisture-proof packaging, can be processed without drying; however, it is always recommended drying the product that comes from a large package (e.g. Octabin). The moisture content suggested for the injection molding process should be lower than 0.15%, according to the grade and to the molded part characteristics. The materials containing flame retardants should have moisture content below 0.10%. Red phosphorous containing grades must always be dried below 0.08%. The drying time depends on the moisture content and the drying conditions. Typically, 4-8 hours at 80-90°C using dehumidified air (dew point of -20°C) are suitable conditions for a starting moisture content of 0.20%-0.40%.

Processing

The following conditions apply to a standard injection molding process. Machine temperatures: barrel 265-290°C (PA66), 235-270°C (PA6), nozzle and hot runners up to 300°C (up to 290°C products with flame retardants). Mold temperatures: 60-80°C, (80-100°C highly reinforced grades). Back pressure: typically, 5-10 bar (hydraulic pressure). Temperatures exceeding 300°C and long residence time could lead to additives degradation and brittleness of the material. In case of gas generation in the melt, please verify moisture content and processing temperatures. Usage of regrind is possible depending on the molded part characteristics. For further details, please refer to the document 'Instructions for injection molding' or contact our technical support team.

Postprocessing

PA materials reach their final performance with a water content of about 1.5 to 3.5% by weight, depending on the type. This percentage corresponds to the point of equilibrium between the rates of absorption and desorption of moisture. After molding, in favorable environmental conditions, a part can quickly absorbs moisture up to 0.5-1.0%, while the equilibrium will be reached during its life. A conditioning treatment can accelerate further the initial water absorption of the molded parts. Conditioning is usually carried out in hot and humid environment (for example 50°C, 100% RH), inside climatic chambers. Slight dimensional variations (increase in volume due to the water absorbed) must be considered, especially in unfilled grades. Post-treatments of parts may also include the annealing (60-80°C in oven, up to four hours). This procedure can be useful to relax any internal stresses.

Zytel® 80G30ARX ECO-R 311 BLK1 (DEVELOPMENTAL)

NYLON RESIN

51016040.21023757.21023758

Revised: 2025-07-08 Source: Celanese Materials Database

The above data are for the developmental sample and are subject to change as the product is scaled up.
NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colorants or other additives may cause significant variations in data values. Properties of molded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.
Copyright © 2026 Celanese or its affiliates. All rights reserved.
Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates.