Zytel® FG70G30HSR3 BK309

NYLON RESIN

Zytel® FG70G30HSR3 BK309 is a 30% Glass Reinforced, Heat Stabilized, Polyamide 66

Product information

Resin Identification	PA-GF30	ISO 1043
Part Marking Code	>PA-GF30<	ISO 11469
ISO designation	ISO 16396-PA66,GF30,M1CGHRW,S14-100	

Rheological properties

	dry/cond.		
Molding shrinkage, parallel	0.2 / -	%	ISO 294-4, 2577
Molding shrinkage, normal	1.0 / -	%	ISO 294-4, 2577

Typical mechanical properties

	dry/cond.		
Tensile modulus	1.45E6 / 1.02E6	psi	ISO 527-1/-2
Tensile stress at break, 5mm/min	29000 / 18900	psi	ISO 527-1/-2
Tensile strain at break, 5mm/min	3.1 / 5	%	ISO 527-1/-2
Flexural modulus	1.38E6 / 1.02E6	psi	ISO 178
Flexural strength	42100 / 29000	psi	ISO 178
Charpy impact strength, 23°C	28.5 / 33.3	ftlb/in²	ISO 179/1eU
Charpy impact strength, -30°C	23.8 / -	ftlb/in²	ISO 179/1eU
Charpy notched impact strength, 23°C	5.23 / 6.66	ftlb/in²	ISO 179/1eA
Charpy notched impact strength, -40°C	4.76 / -	ftlb/in²	ISO 179/1eA
Hardness, Rockwell, M-scale	104 / 88		ISO 2039-2
Hardness, Rockwell, R-scale	124 / 117		ISO 2039-2
Ball indentation hardness, H 961/30	39200 / 27100	psi	ISO 2039-1
Multiaxial Impact, Total Energy, 4.5m/s, 2mm	5 / -	Btu	ISO 6603-2

Thermal properties

	dry/cond.		
Melting temperature, 10°C/min	505 / *	°F	ISO 11357-1/-3
Glass transition temperature, 10°C/min	167 / 68	°F	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	482 / *	°F	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	500 / *	°F	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	408 / *	°F	ISO 306
Coefficient of linear thermal expansion (CLTE), parallel	0.16 / *	E-4/°F	ISO 11359-1/-2
Coefficient of linear thermal expansion (CLTE), normal	0.528 / *	E-4/°F	ISO 11359-1/-2
Thermal conductivity of melt	0.22	W/(m K)	ISO 22007-2
Effective thermal diffusivity, flow	6.85E-8	m²/s	ISO 22007-4
Specific heat capacity of melt	2220	J/(kg K)	ISO 22007-4
RTI, electrical, 0.75mm	257	°F	UL 746B
RTI, electrical, 1.5mm	257	°F	UL 746B
RTI, electrical, 3.0mm	257	°F	UL 746B
RTI, impact, 0.75mm	248	°F	UL 746B
RTI, impact, 1.5mm	248	°F	UL 746B
RTI, impact, 3.0mm	248	°F	UL 746B

Zytel® FG70G30HSR3 BK309

NYLON RESIN

RTI, strength, 0.75mm	257	°F	UL 746B
RTI, strength, 1.5mm	257 / *	°F	UL 746B
RTI, strength, 3.0mm	257	°F	UL 746B

Flammability

	dry/cond.		
Burning Behav. at 1.5mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	0.0591 / *	in	IEC 60695-11-10
UL recognition	yes / *		UL 94
Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.0295 / *	in	IEC 60695-11-10
UL recognition	yes / *		UL 94
Oxygen index	24 / *	%	ISO 4589-1/-2
Glow Wire Flammability Index, 1.0mm	1290 / -	°F	IEC 60695-2-12
Glow Wire Flammability Index, 2.0mm	1380 / -	°F	IEC 60695-2-12
Glow Wire Flammability Index, 3.0mm	1470 / -	°F	IEC 60695-2-12
Glow Wire Ignition Temperature, 1.0mm	1340 / -	°F	IEC 60695-2-13
Glow Wire Ignition Temperature, 2.0mm	1340 / -	°F	IEC 60695-2-13
Glow Wire Ignition Temperature, 3.0mm	1430 / -	°F	IEC 60695-2-13
Glow Wire Temperature, No Flame, 3mm	1380 / -	°F	IEC 60335-1
FMVSS Class	B		ISO 3795 (FMVSS 302)
Burning rate, Thickness 1 mm	<80	in/min	ISO 3795 (FMVSS 302)

Electrical properties

	dry/cond.		
Surface resistivity	* / 1E13	Ohm	IEC 62631-3-2

Physical/Other properties

	dry/cond.		
Water absorption, Immersion 24h	1.3 / *	%	Sim. to ISO 62
Density	0.0495 / -	lb/in^3	ISO 1183
Density of melt	74.9	lb/ft^3	

Injection

Drying Recommended	yes	
Drying Temperature	176	°F
Drying Time, Dehumidified Dryer	2 - 4	h
Processing Moisture Content	≤0.2	%
Melt Temperature Optimum	563	°F
Min. melt temperature	545	°F
Max. melt temperature	581	°F
Max. screw tangential speed	≤0.2	m/s
Mold Temperature Optimum	212	°F
Min. mold temperature	122	°F
Max. mold temperature	248	°F
Hold pressure range	7250 - 14500	psi
Hold pressure time	0.0762	s/mil
Hold Pressure Time (h is the max. wall thickness of the part in mm)	h^2+2	s
Ejection temperature	410	°F

Zytel® FG70G30HSR3 BK309

NYLON RESIN

Automotive

OEM	STANDARD
Bosch	N28 BN02-GF122

Characteristics

Processing	Injection Molding
Additives	Release agent
Special characteristics	Heat stabilized or stable to heat, Hydrolysis resistant

Chemical Media Resistance

Acids

- ✔ Acetic Acid (5% by mass), 23°C
- ✔ Citric Acid solution (10% by mass), 23°C
- ✔ Lactic Acid (10% by mass), 23°C
- ✘ Hydrochloric Acid (36% by mass), 23°C
- ✘ Nitric Acid (40% by mass), 23°C
- ✘ Sulfuric Acid (38% by mass), 23°C
- ✘ Sulfuric Acid (5% by mass), 23°C
- ✘ Chromic Acid solution (40% by mass), 23°C

Bases

- ✘ Sodium Hydroxide solution (35% by mass), 23°C
- ✔ Sodium Hydroxide solution (1% by mass), 23°C
- ✔ Ammonium Hydroxide solution (10% by mass), 23°C

Alcohols

- ✔ Isopropyl alcohol, 23°C
- ✔ Methanol, 23°C
- ✔ Ethanol, 23°C

Hydrocarbons

- ✔ n-Hexane, 23°C
- ✔ Toluene, 23°C
- ✔ iso-Octane, 23°C

Ketones

- ✔ Acetone, 23°C

Ethers

- ✔ Diethyl ether, 23°C

Mineral oils

- ✔ SAE 10W40 multigrade motor oil, 23°C
- ✔ SAE 10W40 multigrade motor oil, 130°C
- ✔ SAE 80/90 hypoid-gear oil, 130°C
- ✔ Insulating Oil, 23°C

Standard Fuels

- ✔ ISO 1817 Liquid 1 - E5, 60°C
- ✔ ISO 1817 Liquid 2 - M15E4, 60°C

Zytel® FG70G30HSR3 BK309

NYLON RESIN

- ✔ ISO 1817 Liquid 3 - M3E7, 60°C
- ✔ ISO 1817 Liquid 4 - M15, 60°C
- ✔ Standard fuel without alcohol (pref. ISO 1817 Liquid C), 23°C
- ✔ Standard fuel with alcohol (pref. ISO 1817 Liquid 4), 23°C
- ✔ Diesel fuel (pref. ISO 1817 Liquid F), 23°C
- ✘ Diesel fuel (pref. ISO 1817 Liquid F), 90°C
- ✘ Diesel fuel (pref. ISO 1817 Liquid F), >90°C

Salt solutions

- ✔ Sodium Chloride solution (10% by mass), 23°C
- ✘ Sodium Hypochlorite solution (10% by mass), 23°C
- ✔ Sodium Carbonate solution (20% by mass), 23°C
- ✔ Sodium Carbonate solution (2% by mass), 23°C
- ✘ Zinc Chloride solution (50% by mass), 23°C

Other

- ✔ Ethyl Acetate, 23°C
- ✔ Hydrogen peroxide, 23°C
- ✔ DOT No. 4 Brake fluid, 130°C
- ✔ Ethylene Glycol (50% by mass) in water, 108°C
- ✔ 1% nonylphenoxy-polyethyleneoxy ethanol in water, 23°C
- ✔ 50% Oleic acid + 50% Olive Oil, 23°C
- ✔ Water, 23°C
- ✔ Water, 90°C
- ✘ Phenol solution (5% by mass), 23°C

Symbols used:

✔ possibly resistant
Defined as: Supplier has sufficient indication that contact with chemical can be potentially accepted under the intended use conditions and expected service life. Criteria for assessment have to be indicated (e.g. surface aspect, volume change, property change).

✘ not recommended - see explanation
Defined as: Not recommended for general use. However, short-term exposure under certain restricted conditions could be acceptable (e.g. fast cleaning with thorough rinsing, spills, wiping, vapor exposure).

Revised: 2025-04-23 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colorants or other additives may cause significant variations in data values. Properties of molded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.
Copyright © 2026 Celanese or its affiliates. All rights reserved.
Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates.