Zytel® FGFE5171 WT411

NYLON RESIN

Common features of Zytel® nylon resin include mechanical and physical properties such as high mechanical strength, excellent balance of stiffness and toughness, good high temperature performance, good electrical and flammability properties, good abrasion and chemical resistance. In addition, Zytel® nylon resins are available in different modified and reinforced grades to create a wide range of products with tailored properties for specific processes and end-uses. Zytel® nylon resin, including most flame retardant grades, offer the ability to be coloured.

The good melt stability of Zytel® nylon resin normally enables the recycling of properly handled production waste. If recycling is not possible, we recommend, as the preferred option, incineration with energy recovery (-31kJ/g of base polymer) in appropriately equipped installations. For disposal, local regulations have to be observed.

Zytel® nylon resin typically is used in demanding applications in the automotive, furniture, domestic appliances, sporting goods and construction industry.

Zytel® FGFE5171 WT411 is a 33% glass filled nylon 66 resin, white color.

FOOD CONTACT
This product is manufactured according to Good Manufacturing Practice (GMP) principles and generally accepted in food contact applications for EMEA. For details, individual compliance statements are available from our representative.

产品信息

树脂鉴别	PA66-GF33		ISO 1043
制品标识码	>PA66-GF33<		ISO 11469
ISO名称	ISO 16396-PA66,GF33,M1GC,S14-100		

流变性能

	dry/cond.		
粘数	130[1]/*	cm^3/g	ISO 307, 1628
熔体粘度, @ 1000 sec-1, 280°C	190/*	Pa.s	ISO 11443

[1]: in formic acid 90%

机械性能

	dry/cond.		
拉伸模量	10000/-	MPa	ISO 527-1/-2
拉伸断裂应力, 5mm/min	150/-	MPa	ISO 527-1/-2
断裂伸长率, 5mm/min	2.5/-	%	ISO 527-1/-2
简支梁无缺口冲击强度, 23°C	40/-	kJ/m^2	ISO 179/1eU
简支梁缺口冲击强度, 23°C	4.5/-	kJ/m^2	ISO 179/1eA

热性能

	dry/cond.		
熔融温度, 10°C/min	262/*	°C	ISO 11357-1/-3
热变形温度, 1.8 MPa	246/*	°C	ISO 75-1/-2
相对温度指数，电气, 0.75mm	130	°C	UL 746B
相对温度指数，电气, 1.5mm	130	°C	UL 746B
相对温度指数，电气, 3.0mm	130	°C	UL 746B
相对温度指数，冲击, 0.75mm	120	°C	UL 746B
相对温度指数，冲击, 1.5mm	120	°C	UL 746B
相对温度指数，冲击, 3.0mm	120	°C	UL 746B
相对温度指数，强度, 0.75mm	130	°C	UL 746B
相对温度指数，强度, 1.5mm	130/*	°C	UL 746B
相对温度指数，强度, 3.0mm	130	°C	UL 746B

Zytel® FGFE5171 WT411

NYLON RESIN

阻燃性能

	dry/cond.		
1.5mm名义厚度时的阻燃性	HB/*	class	IEC 60695-11-10
测试用试样的厚度	1.5/*	mm	IEC 60695-11-10
UL认证	yes/*		UL 94
厚度为h时的阻燃性	HB/*	class	IEC 60695-11-10
测试用试样的厚度	0.71/*	mm	IEC 60695-11-10
UL认证	yes/*		UL 94

电性能

	dry/cond.		
相对漏电起痕指数	600/-		IEC 60112

其它性能

	dry/cond.		
密度	1410/-	kg/m³	ISO 1183

注塑

建议干燥	是	
干燥温度	80	°C
干燥时间，除湿干燥机	2 - 4	h
加工前水分含量	≤ 0.2	%
最优熔体温度	295	°C
最低熔体温度***	285	°C
最高熔体温度	305	°C
螺杆最大切线速度	≤ 0.2	m/s
最优模具温度	100	°C
最低模具温度	70	°C
最高模具温度	120	°C
保压范围	50 - 100	MPa
保压时间	3	s/mm
保压时间 (h表示部件的最大壁厚mm)	h²+2	s
顶出温度	210	°C

特性

加工方法	注塑

Revised: 2025-07-16 Source: Celanese Materials Database

用户须知： 所示数值基于实验室试样测试，代表本色材料标准属性范围内的数据。这些数值本身并不能作为任何部件设计的充分依据，且不旨在用于确定最大值、最小值或规格值范围。着色剂或其他添加剂可能会导致数据值的显著变化。模塑部件的性能会受到多种因素的影响，包括但不限于材料选择、添加剂、部件设计、加工条件和环境暴露。除了那些明确标识为医用级的产品（包括 MT® 产品标识或其他标识），塞拉尼斯的产品不旨在用于医疗或牙科植入。无论产品名称如何，确定特定材料和部件设计是否适用于用户所拟的任何用途以及使用方式是用户自身的责任，用户必须保证后续加工的材料满足其特定产品或用途的需要。据我们所知，本出版物中包含的信息是准确的；但是，我们对此处信息的准确性和完整性不承担任何责任。本出版物中包含的信息不应被视为对我们产品特定性能的承诺或保证。用户应自行负责调查使用本出版物中提及的材料是否侵犯了任何现有专利。此外，考虑到可能产生的不良影响，有必要将人类与许多材料的接触降至最低实际限度。对于本出版物中提到的任何危害，我们既不建议也不保证这些危害是唯一存在的危害。我们建议，打算依赖本出版物中的任何建议或使用本出版物中提及的任何设备、加工技术或材料的人，应确信他们能够满足所有适用的安全和健康标准。我们强烈建议用户在处理每种材料时，都要寻求并遵守制造商的最新说明，并且只委托受过适当培训的人员来处理这些材料。请拨打所列电话号码，了解更多技术信息。在尝试处理我们的产品之前，请致电客户服务部索取相应的材料安全数据表 (MSDS)。
(Copyright) 2026 塞拉尼斯或其附属公司。保留所有权利。
除非另有说明，Celanese®、注册的 C-ball 设计和本文中标有 ®、TM、SM 的所有其他商标均为 Celanese 或其附属公司的商标。