Zytel® ST801A NC010A

NYLON RESIN

Zytel® ST801A NC010A is an Unreinforced, Super Toughened, partially UV stabilized,Polyamide 66

Product information

Resin Identification	PA66-HI	ISO 1043
Part Marking Code	>PA66-HI<	ISO 11469
ISO designation	ISO 16396-PA66-I,,M1G1NR,S12-020	

Rheological properties

	dry/cond.		
Viscosity number	3600 / *	in³/lb	ISO 307, 1628
Molding shrinkage, parallel	1.8 / -	%	ISO 294-4, 2577
Molding shrinkage, normal	1.4 / -	%	ISO 294-4, 2577

Typical mechanical properties

	dry/cond.		
Tensile modulus	290000 / 131000	psi	ISO 527-1/-2
Tensile stress at 50% strain	7110 / 6380	psi	ISO 527-1/-2
Flexural modulus	261000 / 102000	psi	ISO 178
Tensile creep modulus, 1h	* / 116000	psi	ISO 899-1
Tensile creep modulus, 1000h	* / 102000	psi	ISO 899-1
Charpy impact strength, 23°C	- / N	ftlb/in²	ISO 179/1eU
Charpy notched impact strength, 23°C	33.3 / 47.6[P]	ftlb/in²	ISO 179/1eA
Charpy notched impact strength, -30°C	9.51 / 9.51	ftlb/in²	ISO 179/1eA
Izod notched impact strength, 23°C	38.1 / 42.8	ftlb/in²	ISO 180/1A
Izod notched impact strength, -30°C	7.14 / 7.14	ftlb/in²	ISO 180/1A
Izod notched impact strength, -40°C	9.51 / 8.09	ftlb/in²	ISO 180/1A

[P]: Partial Break

Thermal properties

	dry/cond.		
Melting temperature, 10°C/min	504 / *	°F	ISO 11357-1/-3
Glass transition temperature, 10°C/min	167 / 68	°F	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	145 / *	°F	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	315 / *	°F	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	401 / *	°F	ISO 306
Coefficient of linear thermal expansion (CLTE), parallel	0.78 / *	E-4/°F	ISO 11359-1/-2
Coefficient of linear thermal expansion (CLTE), Parallel, 23-55°C(73-130°F)	0.778 / -	E-4/°F	ASTM E 831
Coefficient of linear thermal expansion (CLTE), parallel, -40-23°C	0.611 / *	E-4/°F	ISO 11359-1/-2
Coefficient of linear thermal expansion (CLTE), parallel, 55-160°C	0.889 / *	E-4/°F	ISO 11359-1/-2
Coefficient of linear thermal expansion (CLTE), normal	0.722 / *	E-4/°F	ISO 11359-1/-2
Coefficient of linear thermal expansion (CLTE), Normal,23-55°C (73-130°F)	0.722 / -	E-4/°F	ASTM E 831
Coefficient of linear thermal expansion (CLTE), normal, -40-23°C	0.611 / *	E-4/°F	ISO 11359-1/-2

Zytel® ST801A NC010A

NYLON RESIN

Coefficient of linear thermal expansion (CLTE), normal, 55-160 °C	0.722 / *	E-4/°F	ISO 11359-1/-2
RTI, electrical, 0.75mm	257	°F	UL 746B
RTI, electrical, 1.5mm	257	°F	UL 746B
RTI, electrical, 3.0mm	257	°F	UL 746B
RTI, impact, 0.75mm	167	°F	UL 746B
RTI, impact, 1.5mm	167	°F	UL 746B
RTI, impact, 3.0mm	167	°F	UL 746B
RTI, strength, 0.75mm	185	°F	UL 746B
RTI, strength, 1.5mm	185 / *	°F	UL 746B
RTI, strength, 3.0mm	185	°F	UL 746B

Flammability

	dry/cond.		
Burning Behav. at 1.5mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	0.0591 / *	in	IEC 60695-11-10
UL recognition	yes / *		UL 94
Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.0319 / *	in	IEC 60695-11-10
UL recognition	yes / *		UL 94
Oxygen index	20 / *	%	ISO 4589-1/-2
Hot Wire Ignition, 1.5mm	15 / *	s	UL 746A
Hot Wire Ignition, 3mm	20 / *	s	UL 746A
FMVSS Class	B		ISO 3795 (FMVSS 302)
Burning rate, Thickness 1 mm	<80	in/min	ISO 3795 (FMVSS 302)

Electrical properties

	dry/cond.		
Relative permittivity, 100Hz	3.5 / 5.9		IEC 62631-2-1
Relative permittivity, 1MHz	3.3 / 3.5		IEC 62631-2-1
Dissipation factor, 100Hz	50 / 1580	E-4	IEC 62631-2-1
Dissipation factor, 1MHz	100 / 380	E-4	IEC 62631-2-1
Volume resistivity	>1E13 / 8.7E10	Ohm.m	IEC 62631-3-1
Surface resistivity	* / 1E12	Ohm	IEC 62631-3-2
Electric strength	635 / -	kV/in	IEC 60243-1
Comparative tracking index	600 / -		IEC 60112
Electric Strength, Short Time, 2mm	635 / 660	V/mil	IEC 60243-1
High Amperage Arc Ignition Resistance, 1.5 mm	200[1] / *	arcs	UL 746A
High Amperage Arc Ignition Category, 1.5 mm	200[1] / *	class	UL 746A

[1]: >200

Physical/Other properties

	dry/cond.		
Humidity absorption, 2mm	2 / *	%	Sim. to ISO 62
Water absorption, 2mm	6.5 / *	%	Sim. to ISO 62
Water absorption, Immersion 24h	1.1 / *	%	Sim. to ISO 62
Density	0.0386 / -	lb/in³	ISO 1183

Zytel® ST801A NC010A

NYLON RESIN

Injection

Drying Recommended	yes	
Drying Temperature	176	°F
Drying Time, Dehumidified Dryer	2 - 4	h
Processing Moisture Content	≤0.2	%
Melt Temperature Optimum	554	°F
Min. melt temperature	536	°F
Max. melt temperature	572	°F
Max. screw tangential speed	≤0.3	m/s
Mold Temperature Optimum	176	°F
Min. mold temperature	122	°F
Max. mold temperature	212	°F
Hold pressure range	7250 - 14500	psi
Hold pressure time	0.102	s/mil
Hold Pressure Time (h is the max. wall thickness of the part in mm)	h^2+2	s
Ejection temperature	374	°F

Extrusion

Drying Temperature	176	°F
Drying Time, Dehumidified Dryer	3 - 4	h
Processing Moisture Content	≤0.06	%
Melt Temperature Optimum	536	°F
Melt Temperature Range	527 - 554	°F

Automotive

OEM	STANDARD	ADDITIONAL INFORMATION
Hyundai	MS211-46 Type C-2	
Mercedes-Benz	DBL5404.00 PA6	
Mercedes-Benz	DBL5410.01 PA66-I	
Stellantis - Chrysler	MS.50017 / CPN-2959	Natural


Characteristics

Processing	Injection Molding, Film Extrusion, Extrusion, Sheet Extrusion, Other Extrusion, Coating, Casting
Additives	Release agent
Special characteristics	High impact or impact modified, U.V. stabilized or stable to weather

Zytel® ST801A NC010A

NYLON RESIN


Viscosity-shear rate



Zytel® ST801A NC010A

NYLON RESIN

Shearstress-shear rate



Revised: 2025-04-23 Source: Celanese Materials Database

Zytel® ST801A NC010A

NYLON RESIN

Chemical Media Resistance

Acids

- ✔ Acetic Acid (5% by mass), 23°C
- ✔ Citric Acid solution (10% by mass), 23°C
- ✔ Lactic Acid (10% by mass), 23°C
- ✘ Hydrochloric Acid (36% by mass), 23°C
- ✘ Nitric Acid (40% by mass), 23°C
- ✘ Sulfuric Acid (38% by mass), 23°C
- ✘ Sulfuric Acid (5% by mass), 23°C
- ✘ Chromic Acid solution (40% by mass), 23°C

Bases

- ✘ Sodium Hydroxide solution (35% by mass), 23°C
- ✔ Sodium Hydroxide solution (1% by mass), 23°C
- ✔ Ammonium Hydroxide solution (10% by mass), 23°C

Alcohols

- ✔ Isopropyl alcohol, 23°C
- ✔ Methanol, 23°C
- ✔ Ethanol, 23°C

Hydrocarbons

- ✔ n-Hexane, 23°C
- ✔ Toluene, 23°C
- ✔ iso-Octane, 23°C

Ketones

- ✔ Acetone, 23°C

Ethers

- ✔ Diethyl ether, 23°C

Mineral oils

- ✔ SAE 10W40 multigrade motor oil, 23°C
- ✘ SAE 10W40 multigrade motor oil, 130°C
- ✘ SAE 80/90 hypoid-gear oil, 130°C
- ✔ Insulating Oil, 23°C

Standard Fuels

- ✔ ISO 1817 Liquid 1 - E5, 60°C
- ✔ ISO 1817 Liquid 2 - M15E4, 60°C
- ✔ ISO 1817 Liquid 3 - M3E7, 60°C
- ✔ ISO 1817 Liquid 4 - M15, 60°C
- ✔ Standard fuel without alcohol (pref. ISO 1817 Liquid C), 23°C
- ✔ Standard fuel with alcohol (pref. ISO 1817 Liquid 4), 23°C
- ✔ Diesel fuel (pref. ISO 1817 Liquid F), 23°C
- ✘ Diesel fuel (pref. ISO 1817 Liquid F), 90°C
- ✘ Diesel fuel (pref. ISO 1817 Liquid F), >90°C

Salt solutions

- ✔ Sodium Chloride solution (10% by mass), 23°C
- ✘ Sodium Hypochlorite solution (10% by mass), 23°C

Zytel® ST801A NC010A

NYLON RESIN

- ✔ Sodium Carbonate solution (20% by mass), 23°C
- ✔ Sodium Carbonate solution (2% by mass), 23°C
- ✘ Zinc Chloride solution (50% by mass), 23°C

Other

- ✔ Ethyl Acetate, 23°C
- ✘ Hydrogen peroxide, 23°C
- ✘ DOT No. 4 Brake fluid, 130°C
- ✘ Ethylene Glycol (50% by mass) in water, 108°C
- ✔ 1% nonylphenoxy-polyethyleneoxy ethanol in water, 23°C
- ✔ 50% Oleic acid + 50% Olive Oil, 23°C
- ✔ Water, 23°C
- ✔ Water, 90°C
- ✘ Phenol solution (5% by mass), 23°C

Symbols used:

✔ possibly resistant
Defined as: Supplier has sufficient indication that contact with chemical can be potentially accepted under the intended use conditions and expected service life. Criteria for assessment have to be indicated (e.g. surface aspect, volume change, property change).

✘ not recommended - see explanation
Defined as: Not recommended for general use. However, short-term exposure under certain restricted conditions could be acceptable (e.g. fast cleaning with thorough rinsing, spills, wiping, vapor exposure).

Revised: 2025-04-23 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colorants or other additives may cause significant variations in data values. Properties of molded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.
Copyright © 2026 Celanese or its affiliates. All rights reserved.
Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates.