PBT ULTRADUR B 4300 G4

BASF

Reference catalog 2026 - Upgraded Template

Resin Overview (Upgraded Template)

PBT · 聚对苯二甲酸丁二酯 (Upgraded)

This Grade

Manufacturer	BASF
Category	PBT · 聚对苯二甲酸丁二酯 (Upgraded)
Typical Use	Reference grade for 聚对苯二甲酸丁二酯 (Upgraded)

Key Properties (8 metrics)

Density	1.31 g/cm3
MVR (250°C/2.16 kg)	25 cm3/10min
Melting Point (DSC)	228 °C
Tensile Strength at Break	55 MPa
Tensile Modulus	2500 MPa
Elongation at Break	30%
HDT (1.8 MPa)	65 °C
Continuous Use Temperature	140 °C

Key Features

- Good electrical insulation
- High heat resistance for SMT
- Good chemical resistance
- Fast cycle time

Processing Conditions

Melt Temperature	240-275 °C
Mold Temperature	60-100 °C

Drying	4 h @ 120 °C in desiccant dryer
Processing Methods	Injection molding

Typical Applications

- Electrical connectors
- Automotive sensors
- Industrial switches
- Appliance housings

Regulatory & Compliance

- RoHS compliant
- REACH registered
- FDA food contact grades available

> Data from public manufacturer catalogs. Verify before procurement.

Contact
Mr. Mo Hailong (莫海龙) · Business Manager · +86 138 1603 7020 · 13816037020@139.com

© 2026 Shanghai Jinsutong Plastics Co., Ltd. · Reference catalog 2026 - Upgraded Template