CELANEX® 2300A GV1/20FC

CELANEX® PBT

Celanex 2300A GV1/20FC is a general purpose, 20% glass reinforced polybutylene terephthalate with a good balance of mechanical properties and processability for use in food contact applications in Europe. Celanex 2300A GV1/20FC contains an internal lubricant.
Chemical abbreviation according to ISO 1043-1: PBT GF20, Polybutylene terephthalate, 20 % glass fiber reinforced.
Moulding compound ISO 7792-1 PBT, MGMR, 08-070, GF20

Product information

Resin Identification	PBT-GF20	ISO 1043
Part Marking Code	>PBT-GF20<	ISO 11469

Rheological properties

Melt volume-flow rate	14	cm^3/10min	ISO 1133
Temperature	482	°F	
Load	4.76	lb	
Molding shrinkage range, parallel	0.4 - 0.5	%	ISO 294-4, 2577
Molding shrinkage range, normal	1 - 1.2	%	ISO 294-4, 2577

Typical mechanical properties

Tensile modulus	1.07E6	psi	ISO 527-1/-2
Tensile stress at break, 5mm/min	18100	psi	ISO 527-1/-2
Tensile strain at break, 5mm/min	3	%	ISO 527-1/-2
Flexural strength	24700	psi	ISO 178
Flexural strain at failure	3	%	ISO 178
Tensile creep modulus, 1h	899000	psi	ISO 899-1
Tensile creep modulus, 1000h	696000	psi	ISO 899-1
Charpy impact strength, 23°C	21.9	$ftlb/in^2$	ISO 179/1eU
Charpy impact strength, -30°C	20.5	$ftlb/in^2$	ISO 179/1eU
Charpy notched impact strength, 23°C	3.57	$ftlb/in^2$	ISO 179/1eA
Charpy notched impact strength, -30°C	3.33	$ftlb/in^2$	ISO 179/1eA
Ball indentation hardness, H 961/30	27600	psi	ISO 2039-1

Thermal properties

Melting temperature, 10°C/min	437	°F	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	383	°F	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	428	°F	ISO 75-1/-2
Temperature of deflection under load, 8 MPa	212	°F	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	419	°F	ISO 306
Coefficient of linear thermal expansion (CLTE), parallel	0.19	E-4/°F	ISO 11359-1/-2
Thermal conductivity of melt	0.156	W/(m K)	ISO 22007-2
Specific heat capacity of melt	1840	J/(kg K)	ISO 22007-4

Flammability

Burning Behav. at 1.5mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	0.0591	in	IEC 60695-11-10
Oxygen index	20	%	ISO 4589-1/-2

CELANEX® 2300A GV1/20FC

CELANEX® PBT

Electrical properties

Relative permittivity, 100Hz	4		IEC 62631-2-1
Relative permittivity, 1MHz	4		IEC 62631-2-1
Dissipation factor, 100Hz	16	E-4	IEC 62631-2-1
Dissipation factor, 1MHz	190	E-4	IEC 62631-2-1
Volume resistivity	>1E13	Ohm.m	IEC 62631-3-1
Surface resistivity	>1E15	Ohm	IEC 62631-3-2
Electric strength	762	kV/in	IEC 60243-1
Comparative tracking index	350		IEC 60112

Physical/Other properties

Humidity absorption, 2mm	0.15	%	Sim. to ISO 62
Water absorption, 2mm	0.4	%	Sim. to ISO 62
Density	0.0523	lb/in^3	ISO 1183
Density of melt	76.8	lb/ft^3	

Injection

Drying Recommended	yes	
Drying Temperature	284	°F
Drying Time, Dehumidified Dryer	4 - 6	h
Processing Moisture Content	≤0.02	%
Melt Temperature Optimum	482	°F
Min. melt temperature	464	°F
Max. melt temperature	500	°F
Max. screw tangential speed	0.1 - 0.3	m/s
Mold Temperature Optimum	176	°F
Min. mold temperature	140	°F
Max. mold temperature	266	°F
Ejection temperature	428	°F

Characteristics

Processing	Injection Molding
Additives	Release agent
Special characteristics	Heat stabilized or stable to heat

Additional information

Injection molding

To minimize the volatile content in the final product, dry the resin to ≤0.01% water content. In injection molding, use the lowest possible melt temperature (recommended 240 °C) and shortest feasible residence time (recommended 2-3 minutes). Store the parts in a ventilated, clean area before use. If assistance is needed please contact your Celanese account representative.

These recommendations are based on internal Celanese testing. For drying and injection molding conditions outside the above parameters, customer must test for and verify suitably low volatiles emissions on molded articles to confirm the final product is suitably pure for its intended use.

CELANEX® 2300A GV1/20FC

CELANEX® PBT

Processing Notes

CELANEX® 2300A GV1/20FC

CELANEX® PBT


Pre-Drying

To avoid hydrolytic degradation during processing, CELANEX resins have to be dried to a moisture level equal to or less than 0.01%. Drying should be done in a dehumidifying hopper dryer capable of dewpoints <-40°C (-40°F) at 140°C (284°F) for 4-6 hours.

Storage

For subsequent storage of the material in the dryer until processed (<= 60 h) it is necessary to lower the temperature to 100° C.


Viscosity-shear rate



CELANEX® 2300A GV1/20FC

CELANEX® PBT


Shearstress-shear rate



CELANEX® 2300A GV1/20FC

CELANEX® PBT


Dynamic Shear modulus-temperature



CELANEX® 2300A GV1/20FC

CELANEX® PBT


Stress-strain



CELANEX® 2300A GV1/20FC

CELANEX® PBT


Secant modulus-strain



CELANEX® 2300A GV1/20FC

CELANEX® PBT


Stress-strain (isochronous) 73.4 °F



CELANEX® 2300A GV1/20FC

CELANEX® PBT

Creep modulus-time 73.4 °F



Revised: 2026-05-12 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colorants or other additives may cause significant variations in data values. Properties of molded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.
Copyright © 2026 Celanese or its affiliates. All rights reserved.
Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates.