CELANEX® 3300

CELANEX® PBT

Celanex 3300 is a general purpose, 30% glass reinforced, polybutylene terephthalate that offers a superior combination of mechanical, electrical, and thermal properties. This grade provides outstanding processability and good chemical resistance. Celanex 3300 is a high flow material.

Product information

Resin Identification	PBT-GF30	ISO 1043
Part Marking Code	>PBT-GF30<	ISO 11469

Rheological properties

Melt volume-flow rate	13	cm^3/10min	ISO 1133
Temperature	482	°F	
Load	4.76	lb	
Melt mass-flow rate	17	g/10min	ISO 1133
Melt mass-flow rate, Temperature	482	°F	
Melt mass-flow rate, Load	4.76	lb	
Viscosity number	2770	in^3/lb	ISO 307, 1628
Intrinsic viscosity	0.75		ISO 307, 1628
Molding shrinkage range, parallel	0.3 - 0.7	%	ISO 294-4, 2577
Molding shrinkage range, normal	0.7 - 1.1	%	ISO 294-4, 2577

Typical mechanical properties

Shore D hardness, 15s	84		ISO 48-4 / ISO 868
Tensile modulus	1.45E6	psi	ISO 527-1/-2
Tensile stress at break, 5mm/min	19600	psi	ISO 527-1/-2
Tensile strain at break, 5mm/min	2.5	%	ISO 527-1/-2
Flexural modulus	1.41E6	psi	ISO 178
Flexural strength	30500	psi	ISO 178
Compressive strength	23100[DS]	psi	ISO 604
Charpy impact strength, 23°C	21.9	$ftlb/in^2$	ISO 179/1eU
Charpy impact strength, -30°C	21.4	$ftlb/in^2$	ISO 179/1eU
Charpy notched impact strength, 23°C	4.04	$ftlb/in^2$	ISO 179/1eA
Charpy notched impact strength, -30°C	4.04	$ftlb/in^2$	ISO 179/1eA
Izod notched impact strength, 23°C	3.57	$ftlb/in^2$	ISO 180/1A
Izod impact strength, 23°C	11.4	$ftlb/in^2$	ISO 180/1U
Hardness, Rockwell, M-scale	90		ISO 2039-2
Poisson's ratio	0.43		

[DS]: Derived from similar grade

Thermal properties

Melting temperature, 10°C/min	437	°F	ISO 11357-1/-3
Glass transition temperature, 10°C/min	140	°F	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	401	°F	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	437	°F	ISO 75-1/-2
Temperature of deflection under load, 8 MPa	302	°F	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	428	°F	ISO 306
Coefficient of linear thermal expansion (CLTE), parallel	0.14	E-4/°F	ISO 11359-1/-2
Coefficient of linear thermal expansion (CLTE), normal	0.556	E-4/°F	ISO 11359-1/-2

CELANEX® 3300

CELANEX® PBT

Flammability

Burning Behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.0280	in	IEC 60695-11-10
Oxygen index	20	%	ISO 4589-1/-2

Electrical properties

Relative permittivity, 100Hz	4.5		IEC 62631-2-1
Relative permittivity, 1MHz	4.1		IEC 62631-2-1
Dissipation factor, 100Hz	22	E-4	IEC 62631-2-1
Dissipation factor, 1MHz	160	E-4	IEC 62631-2-1
Volume resistivity	>1E13	Ohm.m	IEC 62631-3-1
Surface resistivity	>1E15	Ohm	IEC 62631-3-2
Electric strength	787	kV/in	IEC 60243-1
Comparative tracking index	425		IEC 60112
Arc Resistance	125	s	UL 746B

Physical/Other properties

Humidity absorption, 2mm	0.16	%	Sim. to ISO 62
Water absorption, 2mm	0.4	%	Sim. to ISO 62
Density	0.0552	lb/in^3	ISO 1183

Emissions

Emission of organic compounds	20	µgC/g	VDA 277

Injection

Drying Recommended	yes	
Drying Temperature	248	°F
Drying Time, Dehumidified Dryer	4 - 6	h
Processing Moisture Content	≤0.02	%
Melt Temperature Optimum	482	°F
Min. melt temperature	464	°F
Max. melt temperature	500	°F
Max. screw tangential speed	0.1 - 0.3	m/s
Mold Temperature Optimum	176	°F
Min. mold temperature	140	°F
Max. mold temperature	266	°F

Automotive

OEM	STANDARD	ADDITIONAL INFORMATION
Bosch	N28 BN07-GF028	Natural
Bosch	N28 BN07-GF028	Black
Ford	WSS-M4D725-B1	
Ford	WSS-M4D929-A3	Natural
General Motors	GMW16733P-PBT-GF30	Natural

CELANEX® 3300

CELANEX® PBT

General Motors	GMW16733P-PBT-GF30	Black
Stellantis - Chrysler	MS.50103 / CPN-2252	Natural
Stellantis - Chrysler	MS.50103 / CPN-3199	Canod
Stellantis - Chrysler	MS.50103 / CPN-4675	100% COLOR MATCH

Characteristics

Processing	Injection Molding

Additional information

Injection molding

Preprocessing

To avoid hydrolytic degradation during processing, CELANEX resins have to be dried to a moisture level equal to or less than 0.02%. Drying should be done in a dehumidifying hopper dryer capable of dewpoints <-30°F (-34°C) at 250°F (121°C) for 4 hours.

Processing

Rear Temperature 450-470(230-240) deg F (deg C)
Center Temperature 460-480(235-250) deg F (deg C)
Front Temperature 470-500(240-260) deg F (deg C)
Nozzle Temperature 480-500(250-260) deg F (deg C)
Melt Temperature 460-500(235-260) deg F (deg C)
Mold Temperature 150-200(65-93) deg F (deg C)
Back Pressure 0-50 psi
Screw Speed Medium
Injection Speed Fast

Injection speed, injection pressure and holding pressure have to be optimized to the individual article geometry. To avoid material degradation during processing low back pressure and minimum screw speed have to be used. Overheating of the material has to be avoided, in particular for flame retardant grades. Up to 25% clean and dry regrind may be used.

Processing Notes

Pre-Drying

To avoid hydrolytic degradation during processing, CELANEX resins have to be dried to a moisture level equal to or less than 0.02%. Drying should be done in a dehumidifying hopper dryer capable of dewpoints <-40°F (-40°C) at 250°F (121°C) for 4 hours.


Storage

For subsequent storage of the material in the dryer until processed (<= 60 h) it is necessary to lower the temperature to 100° C.

CELANEX® 3300

CELANEX® PBT


Stress-strain



CELANEX® 3300

CELANEX® PBT

Secant modulus-strain



Revised: 2026-03-09 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colorants or other additives may cause significant variations in data values. Properties of molded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.
Copyright © 2026 Celanese or its affiliates. All rights reserved.
Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates.