CELANEX® 4202

CELANEX® PBT

Celanex 4202 is a 15% glass reinforced, impact modified polybutylene terephthalate with excellent surface appearance.

Product information

Resin Identification	PBT-I-GF15	ISO 1043
Part Marking Code	>PBT-I-GF15<	ISO 11469

Rheological properties

Melt mass-flow rate	4.5	g/10min	ISO 1133
Melt mass-flow rate, Temperature	482	°F	
Melt mass-flow rate, Load	4.76	lb	
Molding shrinkage, parallel	0.4	%	ISO 294-4, 2577
Molding shrinkage, normal	0.9	%	ISO 294-4, 2577

Typical mechanical properties

Shore D hardness, 15s	79		ISO 48-4 / ISO 868
Tensile modulus	754000	psi	ISO 527-1/-2
Tensile stress at break, 5mm/min	12500	psi	ISO 527-1/-2
Tensile strain at break, 5mm/min	4.4	%	ISO 527-1/-2
Flexural modulus	740000	psi	ISO 178
Flexural strength	20500	psi	ISO 178
Charpy impact strength, 23°C	24.7	ftlb/in²	ISO 179/1eU
Charpy impact strength, -30°C	17.6	ftlb/in²	ISO 179/1eU
Charpy notched impact strength, 23°C	5.09	ftlb/in²	ISO 179/1eA
Charpy notched impact strength, -30°C	2.71	ftlb/in²	ISO 179/1eA
Izod notched impact strength, 23°C	5.57	ftlb/in²	ISO 180/1A

Thermal properties

Melting temperature, 10°C/min	437	°F	ISO 11357-1/-3
Glass transition temperature, 10°C/min	111	°F	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	361	°F	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	421	°F	ISO 75-1/-2
Coefficient of linear thermal expansion (CLTE), parallel	0.20	E-4/°F	ISO 11359-1/-2
Coefficient of linear thermal expansion (CLTE), normal	0.556	E-4/°F	ISO 11359-1/-2

Electrical properties

Relative permittivity, 100Hz	3.4		IEC 62631-2-1
Relative permittivity, 1MHz	3.2		IEC 62631-2-1
Dissipation factor, 1MHz	200	E-4	IEC 62631-2-1
Volume resistivity	2E14	Ohm.m	IEC 62631-3-1
Surface resistivity	1E17	Ohm	IEC 62631-3-2
Electric strength	559	kV/in	IEC 60243-1

CELANEX® 4202

CELANEX® PBT

Physical/Other properties

Humidity absorption, 2mm	0.16	%	Sim. to ISO 62
Density	0.0498	lb/in³	ISO 1183

Injection

Drying Recommended	yes	
Drying Temperature	248	°F
Drying Time, Dehumidified Dryer	4	h
Processing Moisture Content	≤0.02	%
Melt Temperature Optimum	482	°F
Min. melt temperature	464	°F
Max. melt temperature	500	°F
Max. screw tangential speed	0.1 - 0.3	m/s
Mold Temperature Optimum	176	°F
Min. mold temperature	140	°F
Max. mold temperature	266	°F

Characteristics

Processing	Injection Molding

Additional information

Injection molding

Preprocessing

To avoid hydrolytic degradation during processing, CELANEX resins have to be dried to a moisture level equal to or less than 0.02%. Drying should be done in a dehumidifying hopper dryer capable of dewpoints <-30°F (-34°C) at 250°F (121°C) for 4 hours.

Processing

Rear Temperature 450-470(230-240) deg F (deg C)
Center Temperature 460-480(235-250) deg F (deg C)
Front Temperature 470-500(240-260) deg F (deg C)
Nozzle Temperature 480-500(250-260) deg F (deg C)
Melt Temperature 460-500(235-260) deg F (deg C)
Mold Temperature 150-200(65-93) deg F (deg C)
Back Pressure 0-50 psi
Screw Speed Medium
Injection Speed Fast

Injection speed, injection pressure and holding pressure have to be optimized to the individual article geometry. To avoid material degradation during processing low back pressure and minimum screw speed have to be used. Overheating of the material has to be avoided, in particular for flame retardant grades. Up to 25% clean and dry regrind may be used.

Processing Notes

Pre-Drying

CELANEX® 4202

CELANEX® PBT

To avoid hydrolytic degradation during processing, CELANEX resins have to be dried to a moisture level equal to or less than 0.02%. Drying should be done in a dehumidifying hopper dryer capable of dewpoints <-40°F (-40°C) at 250°F (121°C) for 4 hours.

Storage

For subsequent storage of the material in the dryer until processed (<= 60 h) it is necessary to lower the temperature to 100° C.

Revised: 2025-05-16 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colorants or other additives may cause significant variations in data values. Properties of molded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.
Copyright © 2026 Celanese or its affiliates. All rights reserved.
Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates.