Crastin® FGS600F40 BK594 (PRELIMINARY)

THERMOPLASTIC POLYESTER RESIN

Crastin® FGS600F40 BK594 is an unreinforced lubricated, low viscosity polybutylene terephthalate resin for injection molding. It has been developed for consideration into applications such as parts for the food industry.

FOOD CONTACT

This product is manufactured according to Good Manufacturing Practice (GMP) principles and generally accepted in food contact applications in Europe and the USA when meeting applicable use conditions. For details, individual compliance statements are available from our representative.

产品信息

树脂鉴别	PBT		ISO 1043
制品标识码	>PBT<		ISO 11469

流变性能

熔体质量流动速率	36	g/10min	ISO 1133
熔体质量流动速率，温度	250	°C	
熔体质量流动速率，负荷	2.16	kg	
模塑收缩率, 平行	1.8	%	ISO 294-4, 2577
模塑收缩率, 垂直	1.8	%	ISO 294-4, 2577

机械性能

拉伸模量	2700	MPa	ISO 527-1/-2
拉伸屈服应力, 50mm/min	58	MPa	ISO 527-1/-2
屈服伸长率, 50mm/min	4	%	ISO 527-1/-2
断裂标称应变	20	%	ISO 527-1/-2
断裂伸长率, 50mm/min	30	%	ISO 527-1/-2
弯曲模量	2500	MPa	ISO 178
简支梁无缺口冲击强度, 23°C	N	kJ/m²	ISO 179/1eU
简支梁缺口冲击强度, 23°C	4	kJ/m²	ISO 179/1eA

热性能

熔融温度, 10°C/min	225	°C	ISO 11357-1/-3
玻璃化转变温度, 10°C/min	55	°C	ISO 11357-1/-3
热变形温度, 1.8 MPa	57	°C	ISO 75-1/-2
线性热膨胀系数, 平行	110[1]	E-6/K	ISO 11359-1/-2
线性热膨胀系数, 垂直	120[1]	E-6/K	ISO 11359-1/-2
熔体导热系数	0.21	W/(m K)	ISO 22007-2
熔体比热容	2110	J/(kg K)	ISO 22007-4

[1]: From Crastin® S600F40 NC010

Crastin® FGS600F40 BK594 (PRELIMINARY)

THERMOPLASTIC POLYESTER RESIN

阻燃性能

1.5mm名义厚度时的阻燃性	HB	class	IEC 60695-11-10
测试用试样的厚度	1.5	mm	IEC 60695-11-10
氧指数	22	%	ISO 4589-1/-2
FMVSS Class	B		ISO 3795 (FMVSS 302)
燃烧速率, 厚度：1毫米	<80	mm/min	ISO 3795 (FMVSS 302)

其它性能

吸湿率, 2mm	0.2	%	类似ISO 62
吸水率, 2mm	0.4	%	类似ISO 62
密度	1320	kg/m³	ISO 1183
熔体密度	1110	kg/m³	

注塑

建议干燥	是	
干燥温度	140	°C
干燥时间，除湿干燥机	4 - 6	h
加工前水分含量	≤ 0.01	%
最优熔体温度	240	°C
最低熔体温度***	240	°C
最高熔体温度	250	°C
最优模具温度	80	°C
最低模具温度	60	°C
最高模具温度	120	°C
保压范围	≥ 60	MPa
保压时间	4	s/mm
保压时间 (h表示部件的最大壁厚mm)	1.5h²+2	s
背压	尽可能低	MPa
顶出温度	170	°C

特性

加工方法	注塑

其他信息

注塑

To minimize the volatile content in the final product, dry the resin to ≤0.01% water content. In injection molding, use the lowest possible melt temperature (recommended 240 °C) and shortest feasible residence time (recommended 2-3 minutes). Store the parts in a ventilated, clean area before use. If assistance is needed please contact your Celanese account representative.

These recommendations are based on internal Celanese testing. For drying and injection molding conditions outside the above parameters, customer must test for and verify suitably low volatiles emissions on molded articles to confirm the final product is suitably pure for its intended use.

加工注意事项

Pre-Drying

To avoid hydrolytic degradation during processing, CRASTIN resins have to be

dried to a moisture level equal to or less than 0.01%. Drying should be done in a dehumidifying hopper dryer capable of dewpoints <-40°C (-40°F) at 140°C (284°F) for 4-6 hours.

Storage

For subsequent storage of the material in the dryer until processed (<= 60 h) it is necessary to lower the temperature to 100° C.

耐化学性

酸类

- ✔ 醋酸 (5g/100g), 23°C
- ✔ 柠檬酸溶液 (10g/100g), 23°C
- ✔ 乳酸 (10g/100g), 23°C
- ✘ 盐酸 (36g/100g), 23°C
- ✘ 硝酸 (40g/100g), 23°C
- ✘ 硫酸 (38g/100g), 23°C
- ✘ 硫酸 (5g/100g), 23°C
- ✘ 铬酸溶液 (40g/100g), 23°C

碱类

- ✘ 氢氧化钠溶液 (35g/100g), 23°C
- ✔ 氢氧化钠溶液 (1g/100g), 23°C
- ✔ 氨水(氢氧化铵) (10g/100g), 23°C

醇类

- ✔ 异丙醇, 23°C
- ✔ 甲醇, 23°C
- ✔ 乙醇, 23°C

碳氢化合物

- ✔ n-乙烷, 23°C
- ✔ 甲苯, 23°C
- ✔ 异辛烷, 23°C

酮类

- ✔ 丙酮, 23°C

醚类

- ✔ (二)乙醚, 23°C

矿物油

- ✔ SAE 10W40号多效润滑油, 23°C
- ✘ SAE 10W40号多效润滑油, 130°C
- ✘ SAE 89/90号变速箱润滑油, 130°C
- ✔ 绝缘油, 23°C

标准燃油

- ✘ ISO 1817 燃油1号, 60°C
- ✘ ISO 1817 燃油2号, 60°C
- ✘ ISO 1817 燃油3号, 60°C

Crastin® FGS600F40 BK594 (PRELIMINARY)

THERMOPLASTIC POLYESTER RESIN

- ✗ ISO 1817 燃油4号, 60°C
- ✓ 不含酒精的标准燃油(优先使用C类ISO 1817 燃油), 23°C
- ✓ 含酒精的标准燃油(优先使用4号ISO 1817 燃油), 23°C
- ✓ 柴油(优先使用F类ISO 1817液体), 23°C
- ✓ 柴油(优先使用F类ISO 1817液体), 90°C
- ✗ 柴油(优先使用F类ISO 1817液体), >90°C

盐溶液

- ✓ 氯化钠溶液(10g/100g) , 23°C
- ✓ 次氯化钠溶液 (10g/100g), 23°C
- ✓ 碳酸钠溶液 (20g/100g) , 23°C
- ✓ 碳酸钠溶液 (2g/100g), 23°C
- ✓ 氯化锌溶液 (50g/100g), 23°C

其它

- ✓ 乙酸乙酯, 23°C
- ✗ 过氧化氢, 23°C
- ✗ DOT4号刹车油, 130°C
- ✗ 乙二醇水溶液 (50g/100g), 108°C
- ✓ 1g/100g 基苯氧- 聚环氧乙烷乙烯水溶液, 23°C
- ✓ 油酸 (50g/100g) + 橄榄油 (50g/100g), 23°C
- ✓ 水, 23°C
- ✗ 去离子水, 90°C
- ✓ 酚溶液(5g/100g), 23°C

Symbols used:

✓ possibly resistant
Defined as: Supplier has sufficient indication that contact with chemical can be potentially accepted under the intended use conditions and expected service life. Criteria for assessment have to be indicated (e.g. surface aspect, volume change, property change).

✗ not recommended - see explanation
Defined as: Not recommended for general use. However, short-term exposure under certain restricted conditions could be acceptable (e.g. fast cleaning with thorough rinsing, spills, wiping, vapor exposure).

Revised: 2025-04-22 Source: Celanese Materials Database

The above data are preliminary and are subject to change as additional data are developed on subsequent lots.
NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.
Copyright © 2026 Celanese or its affiliates. All rights reserved.
Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates.