Crastin® FRHR5315NH NC010 (PRELIMINARY)

THERMOPLASTIC POLYESTER RESIN

Crastin® FRHR5315NH NC010 is a 15% Glass Reinforced, Flame Retardant, Non-Halogenated, Hydrolysis resistant, Polybutylene Terephthalate

产品信息

树脂鉴别	PBT-GF15 FR(40+30)	ISO 1043
制品标识码	>PBT-GF15 FR(40+30)<	ISO 11469

流变性能

熔体体积流动速度	9	cm^3/10min	ISO 1133
温度	250	°C	
负荷	2.16	kg	
模塑收缩率, 平行	0.6	%	ISO 294-4, 2577
模塑收缩率, 垂直	1.3	%	ISO 294-4, 2577

机械性能

拉伸模量	6400	MPa	ISO 527-1/-2
拉伸断裂应力, 5mm/min	72	MPa	ISO 527-1/-2
断裂伸长率, 5mm/min	2.9	%	ISO 527-1/-2
弯曲模量	6400	MPa	ISO 178
弯曲强度	120	MPa	ISO 178
简支梁无缺口冲击强度, 23°C	32	kJ/m^2	ISO 179/1eU
简支梁无缺口冲击强度, -40°C	28	kJ/m^2	ISO 179/1eU
简支梁缺口冲击强度, 23°C	4.6	kJ/m^2	ISO 179/1eA
简支梁缺口冲击强度, -40°C	4.4	kJ/m^2	ISO 179/1eA

热性能

熔融温度, 10°C/min	221	°C	ISO 11357-1/-3
玻璃化转变温度, 10°C/min	60	°C	ISO 11357-1/-3
热变形温度, 1.8 MPa	190	°C	ISO 75-1/-2

阻燃性能

厚度为h时的阻燃性	V-0	class	IEC 60695-11-10
测试用试样的厚度	0.4	mm	IEC 60695-11-10
灼热丝可燃指数, 0.75mm	960	°C	IEC 60695-2-12
灼热丝起燃温度, 0.75mm	750	°C	IEC 60695-2-13

电性能

相对漏电起痕指数	600	IEC 60112

其它性能

密度	1440	kg/m^3	ISO 1183

Crastin® FRHR5315NH NC010 (PRELIMINARY)

THERMOPLASTIC POLYESTER RESIN

注塑

建议干燥	是	
干燥温度	120	°C
干燥时间，除湿干燥机	2 - 4	h
加工前水分含量	≤ 0.04	%
最优熔体温度	250	°C
最低熔体温度***	240	°C
最高熔体温度	260	°C
最优模具温度	80	°C
最低模具温度	60	°C
最高模具温度	130	°C
保压范围	≥ 60	MPa
保压时间	3	s/mm
背压	尽可能低	MPa
顶出温度	170	°C

特性

加工方法	注塑
添加剂	阻燃剂, 无卤/无红磷阻燃剂
特殊性能	阻燃, 耐水解

Revised: 2026-10-08 Source: Celanese Materials Database

The above data are preliminary and are subject to change as additional data are developed on subsequent lots.
NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.
Copyright © 2026 Celanese or its affiliates. All rights reserved.
Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates.