CYCOLOY™ RESIN XCY620S

REGION ASIA

DESCRIPTION

PC/ABS, hydrolytically stable, standard black and natural.

TYPICAL PROPERTY VALUES

Revision 20260509

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	60	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	100	%	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	86	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2300	MPa	ASTM D790
IMPACT			
Izod Impact, notched, 23°C	680	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	55	J	ASTM D3763
Instrumented Dart Impact Total Energy, -30°C	65	J	ASTM D3763
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	60	kJ/m²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	129	°C	ASTM D1525
HDT, 0.45 MPa, 3.2 mm, unannealed	128	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	108	°C	ASTM D648
CTE, -40°C to 40°C, flow	7.E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	7.E-05	1/°C	ASTM E831
Ball Pressure Test, 75°C +/- 2°C	PASSES	-	IEC 60695-10-2
Ball Pressure Test, approximate maximum	100	°C	IEC 60695-10-2
Vicat Softening Temp, Rate B/120	130	°C	ISO 306
PHYSICAL			
Specific Gravity	1.14	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.7	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 260°C/5.0 kgf	23	g/10 min	ASTM D1238
Density	1.14	g/cm³	ISO 1183
Water Absorption, (23°C/24hrs)	0.3	%	ISO 62-1
ELECTRICAL			
Volume Resistivity	>1.E+16	Ω.cm	IEC 60093
Surface Resistivity, ROA	>1.E+16	Ω	IEC 60093
Dielectric Strength, in oil, 0.8 mm	39	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 1.6 mm	25	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 3.2 mm	17	kV/mm	IEC 60243-1
INJECTION MOLDING			
Drying Temperature	95 – 105	°C	
Drying Time	2 – 4	Hrs	
Maximum Moisture Content	0.02	%	

© 2026 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Melt Temperature	260 – 290	°C	
Nozzle Temperature	240 – 280	°C	
Front - Zone 3 Temperature	250 – 290	°C	
Middle - Zone 2 Temperature	250 – 290	°C	
Rear - Zone 1 Temperature	230 – 260	°C	
Hopper Temperature	60 – 80	°C	
Mold Temperature	60 – 90	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2026 Copyright by SABIC. All rights reserved