ULTEM™ Resin 2300

DESCRIPTION

ULTEM 2300 resin is a standard flow 30% glass fiber reinforced polyetherimide resin. The material is RoHS compliant and is intrinsically flame retardant without the use of FR modifiers and offers UL94 V0 and 5VA ratings and FAR25.853 performance. The material may offer excellent dimension stability, strength, stiffness and creep resistance up to high temperature due to its high glass transition temperature of 217°C. The material is opaque and can be custom colored.

ISCC+ certified renewable bio-based solutions are available for this grade via differentiated color nomenclature.

GENERAL INFORMATION	
Features	Flame Retardant, Chemical Resistance, Hydrolytic Stability, Low Warpage, Low Smoke and Toxicity, Dielectrics, Amorphous, IR Transparent, Bio-Renewable, Non halogenated flame retardant, Electroplatable, Low ionics/Outgassing/Liquid particle count, Creep resistant, Dimensional stability, High stiffness/Strength, High temperature resistance, No PFAS intentionally added
Fillers	Glass Fiber (Total fluorine >50ppm only from inorganic fluorine)
Polymer Types	Polyetherimide (PEI)
Processing Techniques	Sheet extrusion, Injection Molding, Profile Extrusion, Extrusion, Compression molding
Regional Availability	Europe, Asia, Americas

INDUSTRY	SUB INDUSTRY
Automotive	Heavy Truck, Automotive Under the Hood, Aerospace, Motorcycle, Recreational/Specialty Vehicles
Building and Construction	Building Component, Water Management
Consumer	Consumer Goods, Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance, Furniture
Electrical and Electronics	Energy Management, Drone Solutions, Mobile Phone - Computer - Tablets, Circuit Boards/Additives, Lighting, Printer Copier, Speaker - Earphone, Wireless Communication
Hygiene and Healthcare	Personal and Professional Hygiene, Pharmaceutical Packaging and Drug Delivery, Surgical devices, General Healthcare, Patient Testing
Industrial	Electrical, Material Handling, Textile, Eyewear
Mass Transportation	Rail
Packaging	Industrial Packaging

TYPICAL PROPERTY VALUES

Revision 20260807

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL [1]			
Tensile Stress, break, 5 mm/min	175	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.4	%	ISO 527
Tensile Modulus, 1 mm/min	10500	MPa	ISO 527
Flexural Stress, break, 2 mm/min	240	MPa	ISO 178
Flexural Modulus, 2 mm/min	9600	MPa	ISO 178
Ball Indentation Hardness, H358/30	165	MPa	ISO 2039-1
Hardness, Rockwell M	110	-	ISO 2039-2
Taber Abrasion, CS-17, 1 kg	20	mg/1000cy	SABIC method
Tensile Stress, brk, Type I, 5 mm/min	175	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	2.5	%	ASTM D638
Tensile Modulus, 5 mm/min	10400	MPa	ASTM D638

© 2026 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Flexural Stress, brk, 2.6 mm/min, 100 mm span	230	MPa	ASTM D790
Flexural Modulus, 2.6 mm/min, 100 mm span	9400	MPa	ASTM D790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	250	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	9700	MPa	ASTM D790
Hardness, Rockwell M	114	-	ASTM D785
IMPACT [1]			
Izod impact, notched			
80*10*4 +23°C	10	kJ/m²	ISO 180/1A
80*10*4 -30°C	10	kJ/m²	ISO 180/1A
23°C	90	J/m	ASTM D256
-30°C	80	J/m	ASTM D256
Izod Impact, Unnotched			
80*10*4 +23°C	40	kJ/m²	ISO 180/1U
80*10*4 -30°C	40	kJ/m²	ISO 180/1U
23°C	600	J/m	ASTM D4812
-30°C	600	J/m	ASTM D4812
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	10	kJ/m²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	10	kJ/m²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	40	kJ/m²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*4 sp=62mm	40	kJ/m²	ISO 179/1eU
Izod Impact, Reverse Notched, 3.2 mm	470	J/m	ASTM D256
THERMAL [1]			
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	215	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	210	°C	ISO 75/Af
Vicat Softening Temp, Rate A/50	225	°C	ISO 306
Vicat Softening Temp, Rate B/120	220	°C	ISO 306
Vicat Softening Temp, Rate B/50	213	°C	ISO 306
CTE, -40°C to 150°C, flow	1.8E-05	1/°C	ISO 11359-2
CTE, -40°C to 150°C, xflow	4.8E-05	1/°C	ISO 11359-2
Thermal Conductivity	0.31	W/m-°C	ISO 8302
Ball Pressure Test, 125°C +/- 2°C	PASS	-	IEC 60695-10-2
HDT, 0.45 MPa, 3.2 mm, unannealed	215	°C	ASTM D648
HDT, 0.45 MPa, 6.4 mm, unannealed	212	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	211	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	210	°C	ASTM D648
CTE, -20°C to 150°C, flow	1.8E-05	1/°C	ASTM E831
CTE, -20°C to 150°C, xflow	4.8E-05	1/°C	ASTM E831
Relative Temp Index, Elec [2]	180	°C	UL 746B
Relative Temp Index, Mech w/impact [2]	170	°C	UL 746B
Relative Temp Index, Mech w/o impact [2]	180	°C	UL 746B
PHYSICAL [1]			
Density	1.51	g/cm³	ISO 1183
Moisture Absorption, (23°C/50% RH/24hrs)	0.1	%	ISO 62-4
Moisture Absorption, (23°C/50% RH/Equilibrium)	0.6	%	ISO 62-4
Water Absorption, (23°C/24hrs)	0.16	%	ISO 62-1

© 2026 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Water Absorption, (23°C/saturated)	0.9	%	ISO 62-1
Melt Volume Rate			
360°C/5.0 kg	6	cm³/10 min	ISO 1133
Specific Gravity	1.51	-	ASTM D792
Water Absorption, (23°C/24hrs)	0.16	%	ASTM D570
Water Absorption, (23°C/Saturated)	0.9	%	ASTM D570
Melt Flow Rate			
337°C/6.7 kgf	5	g/10 min	ASTM D1238
Mold Shrinkage, flow, 3.2 mm	0.2 – 0.4	%	SABIC method
ELECTRICAL [1]			
Volume Resistivity	1E+15	Ω.cm	IEC 60093
Surface Resistivity, ROA	>1E+15	Ω	IEC 60093
Dielectric Strength, in oil, 0.8 mm	35	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 1.6 mm	26	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 3.2 mm	15	kV/mm	IEC 60243-1
Relative Permittivity, 50/60 Hz	3.3	-	IEC 60250
Relative Permittivity, 1 MHz	3.4	-	IEC 60250
Dielectric Constant			
1.1 GHz [3]	3.51	-	-
5 GHz [3]	3.59	-	-
10 GHz [3]	3.60	-	-
Dissipation Factor			
50/60 Hz	0.0016	-	IEC 60250
1 MHz	0.0023	-	IEC 60250
1.1 GHz [3]	0.0029	-	-
5 GHz [3]	0.0036	-	-
10 GHz [3]	0.0046	-	-
1 kHz	0.0015	-	ASTM D150
Comparative Tracking Index [4]	150	V	IEC 60112
Comparative Tracking Index, M [4]	100	V	IEC 60112
Volume Resistivity	3.E+16	Ω.cm	ASTM D257
Dielectric Strength, in air, 1.6 mm	24.8	kV/mm	ASTM D149
Dielectric Strength, in oil, 1.6 mm	30.3	kV/mm	ASTM D149
Relative Permittivity, 1 kHz	3.7	-	ASTM D150
Comparative Tracking Index (UL) {PLC} [2]	4	PLC Code	UL 746A
Hot-Wire Ignition (HWI), PLC 1 [2]	≥3	mm	UL 746A
Hot-Wire Ignition (HWI), PLC 3 [2]	≥1.5	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 3 [2]	≥1.5	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 4 [2]	≥3	mm	UL 746A
High Voltage Arc Track Rate {PLC} [2]	3	PLC Code	UL 746A
Arc Resistance, Tungsten {PLC} [2]	6	PLC Code	ASTM D495
FLAME CHARACTERISTICS [2]			
UL Yellow Card Link	E121562-221099	-	-
UL Yellow Card Link 2	E121562-470961	-	-
UL Recognized, 94-5VA Flame Class Rating	≥1.2	mm	UL 94

© 2026 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
UL Recognized, 94V-0 Flame Class Rating	≥0.25	mm	UL 94
Glow Wire Ignitability Temperature, 2.0 mm	900	°C	IEC 60695-2-13
Glow Wire Flammability Index, 2.0 mm	960	°C	IEC 60695-2-12
UV-light, water exposure/immersion	F1	-	UL 746C
Oxygen Index (LOI)	48	%	ISO 4589
Oxygen Index (LOI)	50	%	ASTM D2863
NBS Smoke Density, Flaming, Ds 4 min	1.6	-	ASTM E662
INJECTION MOLDING [5]			
Drying Temperature	150	°C	
Drying Time	4 – 6	Hrs	
Drying Time (Cumulative)	24	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	350 – 410	°C	
Nozzle Temperature	345 – 410	°C	
Front - Zone 3 Temperature	345 – 420	°C	
Middle - Zone 2 Temperature	340 – 410	°C	
Rear - Zone 1 Temperature	330 – 400	°C	
Hopper Temperature	80 – 120	°C	
Mold Temperature	135 – 180	°C	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	
Screw Speed	40 – 70	rpm	
Screw speed (Circumferential speed)	0.15 – 0.25	m/s	
Back Pressure	0.3 – 1.5	MPa	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
(2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.
(3) Based on SPDR testing technique on dry as molded specimens.
(4) Value shown here is based on internal measurement.
(5) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

MORE INFORMATION

For curve data and CAE cards, please visit and register at https://materialfinder.sabic-specialties.com

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2026 Copyright by SABIC. All rights reserved