PEI

Ultem® HP-2200

SABIC

Position #120 · Jinsutong Reference Catalog 2026

Resin Overview

PEI · Healthcare, Autoclavable. Sourced from public manufacturer technical data sheets.

This Grade

Manufacturer	SABIC
Category	PEI · Healthcare, Autoclavable
Typical Use	High-heat medical, autoclavable, transparent

Key Properties

Density	1.27 g/cm³
MVR (360°C/5 kg)	14 cm³/10min
Tensile Strength at Yield	105 MPa
Tensile Modulus	3000 MPa
Elongation at Break	60%
HDT (1.8 MPa)	200 °C
Tg (DMA)	217 °C
Light Transmittance (2mm)	85%

Key Features

- USP Class VI certified
- Autoclavable for 1000+ cycles
- High clarity for medical
- SABIC quality

Processing Conditions

Melt Temperature	340-370 °C
Mold Temperature	140-180 °C
Drying	4 h @ 150 °C in desiccant dryer
Processing Methods	Injection molding

Typical Applications

- Reusable medical devices
- Autoclavable trays
- Sterilization containers
- Surgical instrument handles

Regulatory & Compliance

- USP Class VI
- ISO 10993
- FDA 21 CFR 177.1595

> ⚠ All data sourced from public manufacturer catalogs.

Contact
Mr. Mo Hailong (莫海龙) — Business Manager · +86 138 1603 7020 · 13816037020@139.com
Shanghai Jinsutong Plastics Co., Ltd. · 1st Building, 5601 Yanqian Road, Fengxian District, Shanghai

© 2026 Shanghai Jinsutong Plastics Co., Ltd. · Jinsutong Reference Catalog 2026 · jinsutong.com/grades