PEI

Ultem® HU1000

SABIC

Position #116 • Jinsutong Reference Catalog 2026

Resin Overview

PEI · Healthcare, USP Class VI. Sourced from public manufacturer technical data sheets.

This Grade

Manufacturer	SABIC
Category	PEI · Healthcare, USP Class VI
Typical Use	USP Class VI medical transparent parts

Key Properties

Density	1.27 g/cm³
MVR (360°C/5 kg)	14 cm³/10min
Tensile Strength at Yield	105 MPa
Tensile Modulus	3000 MPa
Elongation at Break	60%
HDT (1.8 MPa)	200 °C
Light Transmittance (2mm)	87%
Sterilization Cycles	1000+ autoclave

Key Features

- USP Class VI certified
- Autoclavable for 1000+ cycles
- High clarity for medical transparent
- SABIC quality

Processing Conditions

Melt Temperature	340-370 °C

Mold Temperature	140-180 °C
Drying	4 h @ 150 °C in desiccant dryer
Processing Methods	Injection molding

Typical Applications

- Reusable medical devices
- Surgical instrument handles
- Medical transparent components
- Sterilization trays

Regulatory & Compliance

- USP Class VI
- ISO 10993
- FDA 21 CFR 177.1595

> ⚠ All data sourced from public manufacturer catalogs.

Contact
Mr. Mo Hailong · +86 138 1603 7020 · 13816037020@139.com

© 2026 Shanghai Jinsutong Plastics Co., Ltd. · jinsutong.com/grades