HOSTAFORM® S 9363 XAP®2

HOSTAFORM®

Hostaform® acetal copolymer grade S 9363 XAP®2 is an impact modified grade for demanding applications. Hostaform® S 9363 XAP®2 provides good impact strength while improving modulus and weld line strength over standard impact modified grades, and also exhibits exceptional low emission performance meeting or exceeding the requirements of many automotive markets. Chemical abbreviation according to ISO 1043-1: POM-HI

Product information

Resin Identification	POM-HI		ISO 1043
Part Marking Code	>POM-HI<		ISO 11469

Rheological properties

Melt volume-flow rate	5.5	cm^3/10min	ISO 1133
Temperature	374	°F	
Load	4.76	lb	
Molding shrinkage, parallel	1.8	%	ISO 294-4, 2577
Molding shrinkage, normal	1.6	%	ISO 294-4, 2577

Typical mechanical properties

Tensile modulus	290000	psi	ISO 527-1/-2
Tensile stress at yield, 50mm/min	7300	psi	ISO 527-1/-2
Tensile strain at yield, 50mm/min	12	%	ISO 527-1/-2
Flexural modulus	290000	psi	ISO 178
Charpy impact strength, 23°C	N	$ftlb/in^2$	ISO 179/1eU
Charpy impact strength, -30°C	N	$ftlb/in^2$	ISO 179/1eU
Charpy notched impact strength, 23°C	6.18	$ftlb/in^2$	ISO 179/1eA
Charpy notched impact strength, -30°C	3.81	$ftlb/in^2$	ISO 179/1eA
Izod notched impact strength, 23°C	6.18	$ftlb/in^2$	ISO 180/1A
Izod notched impact strength, -40°C	3.81	$ftlb/in^2$	ISO 180/1A
Hardness, Rockwell, M-scale	65		ISO 2039-2

Thermal properties

Melting temperature, 10°C/min	329	°F	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	183	°F	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	298	°F	ISO 75-1/-2
Coefficient of linear thermal expansion (CLTE), parallel	0.61	E-4/°F	ISO 11359-1/-2
Coefficient of linear thermal expansion (CLTE), normal	0.611	E-4/°F	ISO 11359-1/-2

Physical/Other properties

Humidity absorption, 2mm	0.25	%	Sim. to ISO 62
Water absorption, 2mm	0.8	%	Sim. to ISO 62
Density	0.0498	lb/in^3	ISO 1183

HOSTAFORM® S 9363 XAP®2

HOSTAFORM®

Injection

Drying Recommended	no	
Drying Temperature	212	°F
Drying Time, Dehumidified Dryer	3 - 4	h
Processing Moisture Content	≤0.2	%
Melt Temperature Optimum	374	°F
Min. melt temperature	356	°F
Max. melt temperature	392	°F
Max. screw tangential speed	≤0.3	m/s
Mold Temperature Optimum	149	°F
Min. mold temperature	140	°F
Max. mold temperature	158	°F
Hold pressure range	8700 - 17400	psi
Hold Pressure Time (h is the max. wall thickness of the part in mm)	$2h^2$-3	s
Back pressure	290	psi

Automotive

OEM	STANDARD	ADDITIONAL INFORMATION
Ford	WSF-M4D618-A	Natural
Li Auto	Q/LiA5310020	2021 (V2)
Mercedes-Benz	DBL5404	BQF
Renault	UB15, No Spec, Special Part Approval, See Your CE Account Manager.	
SAIC Motor	SMTC 5 310 020	

Characteristics

Processing	Injection Molding, Extrusion
Additives	Release agent
Special characteristics	High impact or impact modified, Low emissions

Additional information

Processing Notes


Pre-Drying

Drying is suggested to help achieve low emission performance and to counter if material has contacted moisture through improper storage and handling.

HOSTAFORM® S 9363 XAP®2

HOSTAFORM®


Stress-strain



HOSTAFORM® S 9363 XAP®2

HOSTAFORM®

Secant modulus-strain



Revised: 2025-07-21 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colorants or other additives may cause significant variations in data values. Properties of molded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.
Copyright © 2026 Celanese or its affiliates. All rights reserved.
Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates.