HOSTAFORM® S 9364 XAP®2 ECO-C 772

HOSTAFORM®

Hostaform® acetal copolymer grade S 9364 XAP®2 ECO-C 772 is a highly impact modified grade for demanding applications. Hostaform® S 9364 XAP®2 ECO-C 772 provides a significant improvement in impact strength and flexibility over standard impact modified grades. Hostaform® S 9364 XAP®2 ECO-C 772 exhibits exceptional low emission performance meeting or exceeding the requirements of many automotive markets. Emission according to VDA275 < 5 mg/kg.

Hostaform® S 9364 XAP®2 ECO-C 772 incorporates a minimum of 70% circular content derived from captured carbon dioxide emissions by weight in the finished product through mass balance allocation. The product is a drop-in replacement to the standard grade with the same performance and processing properties and contributes to the displacement of virgin fossil fuel resources. The feedstock utilizing captured carbon dioxide emissions are ISCC CFC certified as low carbon intensity methanol.

产品信息

树脂鉴别	POM-HI		ISO 1043
制品标识码	>POM-HI<		ISO 11469

流变性能

熔体体积流动速度	4	cm^3/10min	ISO 1133
温度	190	°C	
负荷	2.16	kg	
模塑收缩率, 平行	1.6	%	ISO 294-4, 2577
模塑收缩率, 垂直	1.5	%	ISO 294-4, 2577

机械性能

拉伸模量	1650	MPa	ISO 527-1/-2
拉伸屈服应力, 50mm/min	43	MPa	ISO 527-1/-2
屈服伸长率, 50mm/min	16	%	ISO 527-1/-2
弯曲模量	1550	MPa	ISO 178
3.5%应变时的弯曲应力	42	MPa	ISO 178
简支梁无缺口冲击强度, 23°C	N	kJ/m^2	ISO 179/1eU
简支梁无缺口冲击强度, -30°C	N	kJ/m^2	ISO 179/1eU
简支梁缺口冲击强度, 23°C	21	kJ/m^2	ISO 179/1eA
简支梁缺口冲击强度, -30°C	11	kJ/m^2	ISO 179/1eA
悬臂梁缺口冲击强度, 23°C	20	kJ/m^2	ISO 180/1A
悬臂梁缺口冲击强度, -40°C	10.0	kJ/m^2	ISO 180/1A
洛氏硬度, M	48		ISO 2039-2

热性能

熔融温度, 10°C/min	165	°C	ISO 11357-1/-3
热变形温度, 1.8 MPa	75	°C	ISO 75-1/-2
热变形温度, 0.45 MPa	140	°C	ISO 75-1/-2
线性热膨胀系数, 平行	120	E-6/K	ISO 11359-1/-2
线性热膨胀系数, 垂直	110	E-6/K	ISO 11359-1/-2

HOSTAFORM® S 9364 XAP®2 ECO-C 772

HOSTAFORM®

其它性能

吸湿率, 2mm	0.25	%	类似ISO 62
吸水率, 2mm	0.8	%	类似ISO 62
密度	1360	kg/m³	ISO 1183

注塑

建议干燥	否	
干燥温度	100	°C
干燥时间，除湿干燥机	3 - 4	h
加工前水分含量	≤ 0.2	%
最优熔体温度	190	°C
最低熔体温度***	180	°C
最高熔体温度	200	°C
螺杆最大切线速度	≤ 0.3	m/s
最优模具温度	65	°C
最低模具温度	60	°C
最高模具温度	70	°C
保压范围	60 - 120	MPa
保压时间 (h表示部件的最大壁厚mm)	2h²-3	s
背压	2	MPa

挤出成型

干燥温度	90 - 110	°C
干燥时间，除湿干燥机	3 - 4	h
加工前水分含量	≤ 0.2	%
最优熔体温度	185	°C
熔体温度范围	170 - 200	°C

特性

加工方法	注塑, 异型材挤出成型
添加剂	脱模助剂
特殊性能	抗冲改性, 低散发
可持续	碳捕集

其他信息

加工注意事项


Pre-Drying

Drying is suggested to help achieve low emission performance and to counter if material has contacted moisture through improper storage and handling.

HOSTAFORM® S 9364 XAP®2 ECO-C 772

HOSTAFORM®


应力 - 应变



HOSTAFORM® S 9364 XAP®2 ECO-C 772

HOSTAFORM®

正割模量 - 应变



Revised: 2026-01-23 Source: Celanese Materials Database

用户须知： 所示数值基于实验室试样测试，代表本色材料标准属性范围内的数据。这些数值本身并不能作为任何部件设计的充分依据，且不旨在用于确定最大值、最小值或规格值范围。着色剂或其他添加剂可能会导致数据值的显著变化。模塑部件的性能会受到多种因素的影响，包括但不限于材料选择、添加剂、部件设计、加工条件和环境暴露。除了那些明确标识为医用级的产品（包括 MT® 产品标识或其他标识），塞拉尼斯的产品不旨在用于医疗或牙科植入。无论产品名称如何，确定特定材料和部件设计是否适用于用户所拟的任何用途以及使用方式是用户自身的责任，用户必须保证后续加工的材料满足其特定产品或用途的需要。据我们所知，本出版物中包含的信息是准确的；但是，我们对此处信息的准确性和完整性不承担任何责任。本出版物中包含的信息不应被视为对我们产品特定性能的承诺或保证。用户应自行负责调查使用本出版物中提及的材料是否侵犯了任何现有专利。此外，考虑到可能产生的不良影响，有必要将人类与许多材料的接触降至最低实际限度。对于本出版物中提到的任何危害，我们既不建议也不保证这些危害是唯一存在的危害。我们建议，打算依赖本出版物中的任何建议或使用本出版物中提及的任何设备、加工技术或材料的人，应确信他们能够满足所有适用的安全和健康标准。我们强烈建议用户在处理每种材料时，都要寻求并遵守制造商的最新说明，并且只委托受过适当培训的人员来处理这些材料。请拨打所列电话号码，了解更多技术信息。在尝试处理我们的产品之前，请致电客户服务部索取相应的材料安全数据表 (MSDS)。
(Copyright) 2026 塞拉尼斯或其附属公司。保留所有权利。
除非另有说明，Celanese®、注册的 C-ball 设计和本文中标有 ®、TM、SM 的所有其他商标均为 Celanese 或其附属公司的商标。