TALCOPRENE® 1540TLT1

TALCOPRENE®

Polypropylene, homopolymer, 38% mineral filled, high heat stabilization, low fogging

Product information

Resin Identification	PP-T38		ISO 1043
Part Marking Code	>PP-T38<		ISO 11469

Rheological properties

Melt mass-flow rate	14	g/10min	ISO 1133
Melt mass-flow rate, Temperature	446	°F	
Melt mass-flow rate, Load	4.76	lb	
Molding shrinkage, parallel	0.9	%	ISO 294-4, 2577
Molding shrinkage range, parallel	0.9 - 1	%	ISO 294-4, 2577
Molding shrinkage, normal	0.9	%	ISO 294-4, 2577
Molding shrinkage range, normal	0.9 - 1	%	ISO 294-4, 2577

Typical mechanical properties

Tensile modulus	551000	psi	ISO 527-1/-2
Tensile stress at break, 5mm/min	3770	psi	ISO 527-1/-2
Tensile strain at break, 5mm/min	4	%	ISO 527-1/-2
Flexural modulus	537000	psi	ISO 178
Flexural strength	6530	psi	ISO 178
Charpy notched impact strength, 23°C	0.809	ftlb/in²	ISO 179/1eA
Izod notched impact strength, 23°C	1.05	ftlb/in²	ISO 180/1A

Thermal properties

Melting temperature, 10°C/min	327	°F	ISO 11357-1/-3
Vicat softening temperature, 50°C/h 50N	208	°F	ISO 306

Flammability

Burning Behav. at 1.5mm nom. thickn.	HB	class	IEC 60695-11-10
Burning Behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.1260	in	IEC 60695-11-10
FMVSS Class	B		ISO 3795 (FMVSS 302)
Burning rate, Thickness 1 mm	3.62	in/min	ISO 3795 (FMVSS 302)

Physical/Other properties

Density	0.0455	lb/in³	ISO 1183

Automotive

OEM	STANDARD	ADDITIONAL INFORMATION
Mercedes-Benz	No Spec listed	
VW Group	VW 44045	PP8

Revised: 2026-08-12 Source: Celanese Materials Database

TALCOPRENE® 1540TLT1

TALCOPRENE®

Characteristics

Processing	Injection Molding
Special characteristics	Heat stabilized or stable to heat

Additional information

Processing Notes

Storage

This product should be stored in a covered facility and kept away from moisture and heat.

Revised: 2026-08-12 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colorants or other additives may cause significant variations in data values. Properties of molded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.
Copyright © 2026 Celanese or its affiliates. All rights reserved.
Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates.