PP

Moplen® RF365BK

LyondellBasell

Position #106 · Jinsutong Reference Catalog 2026

Resin Overview

PP · 30% Glass Fiber, Black. Sourced from public manufacturer technical data sheets.

This Grade

Manufacturer	LyondellBasell
Category	PP · 30% Glass Fiber, Black
Typical Use	High-modulus structural, automotive

Key Properties

MFR (230°C/2.16 kg)	4 g/10min
Density	1.12 g/cm³
Tensile Strength at Break	85 MPa
Tensile Modulus	6500 MPa
Elongation at Break	3%
HDT (1.8 MPa)	150 °C
Flexural Modulus	6000 MPa
Color	Black

Key Features

- 30% glass for high modulus
- Black pre-compounded
- Suitable for metal replacement
- LyondellBasell quality

Processing Conditions

Melt Temperature	220-260 °C
Mold Temperature	40-80 °C
Drying	2 h @ 80 °C
Processing Methods	Injection molding

Typical Applications

- Automotive structural parts
- Metal replacement
- Industrial components
- Premium automotive parts

Regulatory & Compliance

- RoHS compliant
- REACH registered

> ⚠ All data sourced from public manufacturer catalogs.

Contact
Mr. Mo Hailong (莫海龙) — Business Manager · +86 138 1603 7020 · 13816037020@139.com
Shanghai Jinsutong Plastics Co., Ltd. · 1st Building, 5601 Yanqian Road, Fengxian District, Shanghai

© 2026 Shanghai Jinsutong Plastics Co., Ltd. · Jinsutong Reference Catalog 2026 · jinsutong.com/grades