Zytel® FE150065 NC010 (PRELIMINARY)

LONG CHAIN POLYAMIDE RESIN

Zytel® FE150065 NC010 是一种23% 玻璃微珠/玻纤增强，低密度的尼龙610用于轻量化结构应用。

产品信息

树脂鉴别	PA610-(GB+GF)23		ISO 1043
制品标识码	>PA610-(GB+GF)23<		ISO 11469
ISO名称	ISO 16396-PA610,(GB+GF)23,MNG,S14-040		
生物碳含量	≥ 60[C]	%	ISO 16620-2

[C]: Calculated

流变性能

	dry/cond.		
模塑收缩率, 平行	0.8/-	%	ISO 294-4, 2577
模塑收缩率, 垂直	0.8/-	%	ISO 294-4, 2577

机械性能

	dry/cond.		
拉伸模量	4100/-	MPa	ISO 527-1/-2
拉伸断裂应力, 5mm/min	90/-	MPa	ISO 527-1/-2
断裂伸长率, 5mm/min	4.5/-	%	ISO 527-1/-2
弯曲模量	3600/-	MPa	ISO 178
弯曲强度	130/-	MPa	ISO 178
简支梁无缺口冲击强度, 23°C	38/-	kJ/m²	ISO 179/1eU
简支梁缺口冲击强度, 23°C	5/-	kJ/m²	ISO 179/1eA

热性能

	dry/cond.		
熔融温度, 10°C/min	224/*	°C	ISO 11357-1/-3
热变形温度, 1.8 MPa	170/*	°C	ISO 75-1/-2

阻燃性能

	dry/cond.		
1.5mm名义厚度时的阻燃性	HB/*	class	IEC 60695-11-10

电性能

	dry/cond.		
相对介电常数, 23°C, 10 GHz	2.6[1]/-		ASTM D 2520 B / IPC-TM-650
介质损耗因子, 23°C, 10 GHz	100[1]/-	E-4	ASTM D 2520 B / IPC-TM-650

[1]: measured at 2.45GHz

其它性能

	dry/cond.		
吸湿率, 2mm	1.5/*	%	类似ISO 62
密度	960/-	kg/m³	ISO 1183

Zytel® FE150065 NC010 (PRELIMINARY)

LONG CHAIN POLYAMIDE RESIN

注塑

干燥温度	80 °C
干燥时间，除湿干燥机	2 - 4 h
加工前水分含量	≤ 0.15 %
最优熔体温度	280 °C
最低熔体温度***	270 °C
最高熔体温度	290 °C
最优模具温度	100 °C
最低模具温度	70 °C
最高模具温度	120 °C
保压时间 (h表示部件的最大壁厚mm)	h^2+2 s

特性

加工方法	注塑

Revised: 2026-06-18 Source: Celanese Materials Database

The above data are preliminary and are subject to change as additional data are developed on subsequent lots.
NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.
Copyright © 2026 Celanese or its affiliates. All rights reserved.
Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates.