Zytel® HTN7225GVS GY

HIGH PERFORMANCE POLYAMIDE RESIN

- Zytel® HTN7225GVS GY is a glass fiber reinforced and flame retardant PA.MXD6 grade.
- It has higher mechanical properties, heat resistance and flame retardance. (UL-94 V-0 type)
- It is suitable for applications such as automotive, electrical & electronics, and industrial parts.

Product information

Resin Identification	PAMXD6-GF25	ISO 1043
Part Marking Code	>PAMXD6-GF25<	ISO 11469

Typical mechanical properties

	dry/cond.		
Tensile stress at break, 5mm/min	23900 / -	psi	ISO 527-1/-2
Tensile strain at break, 5mm/min	1.8 / -	%	ISO 527-1/-2
Flexural modulus	1.38E6 / -	psi	ISO 178
Flexural strength	33400 / -	psi	ISO 178
Charpy notched impact strength, 23 °C	3.09 / -	ftlb/in²	ISO 179/1eA

Thermal properties

	dry/cond.		
Melting temperature, 10 °C/min	460 / *	°F	ISO 11357-1/-3

Flammability

	dry/cond.		
Burning Behav. at thickness h	V-0 / *	class	IEC 60695-11-10
Thickness tested	0.0315 / *	in	IEC 60695-11-10

Physical/Other properties

	dry/cond.		
Density	0.0567 / -	lb/in³	ISO 1183

Characteristics

Processing	Injection Molding
Special characteristics	Heat stabilized or stable to heat

Additional information

Injection molding

Preprocessing

The maximum humidity content allowed for the injection molding process is 0.05%. The drying time depends on the initial moisture content and the drying conditions used. Generally 4-6 hours at 80 °C at a dehumidifier dryer or 6-8 hours at 90ºC at a dryer are sufficient.

Processing

The following conditions apply to the normal injection molding process of MAXIMID compounds. Machine temperatures: barrel 280-290 °C (536-554ºF), nozzle and hot runners 280-290 °C (536-554ºF). Mold temperatures: 70-90 °C (158-194ºF). Back pressure: typically 5-10 bar (hydraulic pressure). In case of

Zytel® HTN7225GVS GY

HIGH PERFORMANCE POLYAMIDE RESIN

gas generation in the melt, please verify moisture content and processing temperatures. For further details, please contact our technical support team.

Processing Notes

Pre-Drying

It is recommended to dry material at 80ºC (176ºF) for 4-6h at dehumidified dryer.
It is recommended to dry material at 90ºC (194ºF) for 6-8h at dryer.
suggested max. moisture = 0.05%

Revised: 2025-09-11 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colorants or other additives may cause significant variations in data values. Properties of molded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.
Copyright © 2026 Celanese or its affiliates. All rights reserved.
Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates.