Zytel® HTN51G35HSL NC010

HIGH PERFORMANCE POLYAMIDE RESIN

Zytel® HTN high performance polyamide resins feature high retention of properties upon exposure to elevated temperature, to high moisture, and to harsh chemical environments. Polymer families and grades of Zytel® HTN are tailored to optimize performance as well as processability.

Typical applications with Zytel® HTN include demanding applications in the automotive, electrical and electronics, domestic appliances, and construction industries.

Zytel® HTN51G35HSL NC010 is a 35% glass reinforced, heat stabilized, lubricated, hydrolysis resistant high performance polyamide resin. It is also a PPA resin.

Product information

Resin Identification	PA6T/XT-GF35	ISO 1043
Part Marking Code	>PA6T/XT-GF35<	ISO 11469
Part Marking Code	>PPA-GF35<	SAE J1344
ISO designation	ISO 16396-PA6T/XT,GF35,M1GHNR,S10-120	
Infrared spectrum	available	

Rheological properties

	dry/cond.		
Molding shrinkage, parallel	0.2 / -	%	ISO 294-4, 2577
Molding shrinkage, normal	0.6 / -	%	ISO 294-4, 2577

Typical mechanical properties

	dry/cond.		
Tensile modulus	1.74E6 / 1.74E6	psi	ISO 527-1/-2
Tensile stress at break, 5mm/min	30500 / 30500	psi	ISO 527-1/-2
Tensile strain at break, 5mm/min	2.4 / 2.2	%	ISO 527-1/-2
Flexural modulus	1.49E6 / 1.49E6	psi	ISO 178
Flexural strength	43500 / 42100	psi	ISO 178
Tensile creep modulus, 1h	* / 1.6E6	psi	ISO 899-1
Tensile creep modulus, 1000h	* / 1.38E6	psi	ISO 899-1
Charpy impact strength, 23 °C	28.5 / 26.2	ftlb/in²	ISO 179/1eU
Charpy impact strength, -30 °C	28.5 / 23.8	ftlb/in²	ISO 179/1eU
Charpy notched impact strength, 23 °C	5.23 / 5.23	ftlb/in²	ISO 179/1eA
Charpy notched impact strength, -30 °C	4.76 / 4.76	ftlb/in²	ISO 179/1eA
Charpy notched impact strength, -40 °C	5.23 / -	ftlb/in²	ISO 179/1eA
Izod notched impact strength, 23 °C	5.23 / 5.23	ftlb/in²	ISO 180/1A
Izod notched impact strength, -30 °C	4.76 / 4.76	ftlb/in²	ISO 180/1A
Izod impact strength, -30 °C	23.8 / 19	ftlb/in²	ISO 180/1U
Hardness, Rockwell, M-scale	108 / -		ISO 2039-2
Hardness, Rockwell, R-scale	124 / -		ISO 2039-2

Tribological properties

	dry/cond.	
Coefficient of sliding friction, 1h against steel	- / 0.35	ASTM 1894

Zytel® HTN51G35HSL NC010

HIGH PERFORMANCE POLYAMIDE RESIN

Thermal properties

	dry/cond.		
Melting temperature, 10°C/min	572 / *	°F	ISO 11357-1/-3
Melting temperature, first heat	572 / *	°F	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	507 / *	°F	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	543 / *	°F	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	554 / *	°F	ISO 306
Coefficient of linear thermal expansion (CLTE), parallel	0.10 / *	E-4/°F	ISO 11359-1/-2
Coefficient of linear thermal expansion (CLTE), parallel, -40-23°C	0.1 / *	E-4/°F	ISO 11359-1/-2
Coefficient of linear thermal expansion (CLTE), normal	0.306 / *	E-4/°F	ISO 11359-1/-2
Coefficient of linear thermal expansion (CLTE), normal, -40-23°C	0.306 / *	E-4/°F	ISO 11359-1/-2
Thermal conductivity of melt	0.25	W/(m K)	ISO 22007-2
Specific heat capacity of melt	1840	J/(kg K)	ISO 22007-4
RTI, electrical, 0.75mm	302	°F	UL 746B
RTI, electrical, 1.5mm	302	°F	UL 746B
RTI, electrical, 3.0mm	302	°F	UL 746B
RTI, impact, 0.75mm	257	°F	UL 746B
RTI, impact, 1.5mm	257	°F	UL 746B
RTI, impact, 3.0mm	266	°F	UL 746B
RTI, strength, 0.75mm	266	°F	UL 746B
RTI, strength, 1.5mm	284 / *	°F	UL 746B
RTI, strength, 3.0mm	302	°F	UL 746B

Flammability

	dry/cond.		
Burning Behav. at 1.5mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	0.0591 / *	in	IEC 60695-11-10
UL recognition	yes / *		UL 94
Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.0335 / *	in	IEC 60695-11-10
UL recognition	yes / *		UL 94
Oxygen index	24 / *	%	ISO 4589-1/-2
Glow Wire Flammability Index, 0.75mm	1380 / -	°F	IEC 60695-2-12
Glow Wire Flammability Index, 1.5mm	1380 / -	°F	IEC 60695-2-12
Glow Wire Flammability Index, 3.0mm	1760 / -	°F	IEC 60695-2-12
Glow Wire Ignition Temperature, 1.5mm	1430 / -	°F	IEC 60695-2-13
Glow Wire Ignition Temperature, 3.0mm	1470 / -	°F	IEC 60695-2-13
FMVSS Class	B		ISO 3795 (FMVSS 302)
Burning rate, Thickness 1 mm	0.906	in/min	ISO 3795 (FMVSS 302)

Electrical properties

	dry/cond.		
Relative permittivity, 100Hz	4 / -		IEC 62631-2-1
Relative permittivity, 1MHz	4 / -		IEC 62631-2-1
Dissipation factor, 1MHz	120 / -	E-4	IEC 62631-2-1
Volume resistivity	>1E13 / 1E13	Ohm.m	IEC 62631-3-1
Surface resistivity	* / 1E14	Ohm	IEC 62631-3-2

Zytel® HTN51G35HSL NC010

HIGH PERFORMANCE POLYAMIDE RESIN

Electric strength	914 / 914	kV/in	IEC 60243-1
Comparative tracking index	600 / -		IEC 60112
Dielectric Constant, 1 GHz	3.9 / -		ASTM D 2520 B
Dissipation Factor, 1 GHz	120 / -	E-4	ASTM D 2520 B

Physical/Other properties

	dry/cond.		
Humidity absorption, 2mm	1.4 / *	%	Sim. to ISO 62
Water absorption, 2mm	4 / *	%	Sim. to ISO 62
Water absorption, Immersion 24h	1 / *	%	Sim. to ISO 62
Density	0.0531 / -	lb/in³	ISO 1183
Density of melt	76.8	lb/ft³	

Emissions

Odor test	4	class	VDA 270

Injection

Drying Recommended	yes	
Drying Temperature	212	°F
Drying Time, Dehumidified Dryer	6 - 8	h
Processing Moisture Content	≤0.1	%
Melt Temperature Optimum	617	°F
Min. melt temperature	608	°F
Max. melt temperature	626	°F
Mold Temperature Optimum	293	°F
Min. mold temperature	266[1]	°F
Max. mold temperature	320	°F
Hold Pressure Time (h is the max. wall thickness of the part in mm)	h²+2	s
Ejection temperature	500	°F

[1]: Higher temperature needed for thinner sections.

Automotive

OEM	STANDARD	ADDITIONAL INFORMATION
Ford	WSS-M98P14-A3	
General Motors	GMW16356P-PPA-GF35	Natural
Hyundai	MS941-03 Type N-4	
Stellantis	B62 0300 / 61/213M+/215E+/H113/H115(168h)13/C1B	Natural
Stellantis	MS.50156 / PPA.GF30-35.10000T.7C.HS	CPN4190, 01994_10_00119
Stellantis - Chrysler	MS.50103 / CPN-4190	Natural

Characteristics

Processing	Injection Molding
Additives	Release agent
Special characteristics	Heat stabilized or stable to heat, Hydrolysis resistant


Zytel® HTN51G35HSL NC010

HIGH PERFORMANCE POLYAMIDE RESIN

Additional information

Injection molding	During molding, use proper protective equipment and adequate ventilation. Avoid exposure to fumes and limit the hold up time and temperature of the resin in the machine. Purge degraded resin carefully with HDPE. When lower mold temperatures are used, the initial warpage and shrinkage may be lower, but the surface appearance and chemical resistance may be reduced, and the dimensional change may be greater when parts are subsequently heated.


Viscosity-shear rate



Zytel® HTN51G35HSL NC010

HIGH PERFORMANCE POLYAMIDE RESIN


Shearstress-shear rate



Zytel® HTN51G35HSL NC010

HIGH PERFORMANCE POLYAMIDE RESIN


Dynamic Shear modulus-temperature (dry)



Zytel® HTN51G35HSL NC010

HIGH PERFORMANCE POLYAMIDE RESIN


Stress-strain (dry)



Zytel® HTN51G35HSL NC010

HIGH PERFORMANCE POLYAMIDE RESIN


Stress-strain (cond.)



Zytel® HTN51G35HSL NC010

HIGH PERFORMANCE POLYAMIDE RESIN


Secant modulus-strain (dry)



Zytel® HTN51G35HSL NC010

HIGH PERFORMANCE POLYAMIDE RESIN


Secant modulus-strain (cond.)



Zytel® HTN51G35HSL NC010

HIGH PERFORMANCE POLYAMIDE RESIN


Stress-strain (isochronous) 73.4 °F (cond.)



Zytel® HTN51G35HSL NC010

HIGH PERFORMANCE POLYAMIDE RESIN


Creep modulus-time 73.4 °F (cond.)



Zytel® HTN51G35HSL NC010

HIGH PERFORMANCE POLYAMIDE RESIN


Stress-strain (isochronous) 212°F (dry)



Zytel® HTN51G35HSL NC010

HIGH PERFORMANCE POLYAMIDE RESIN


Creep modulus-time 212°F (dry)



Zytel® HTN51G35HSL NC010

HIGH PERFORMANCE POLYAMIDE RESIN


Stress-strain (isochronous) 302 °F (dry)



Zytel® HTN51G35HSL NC010

HIGH PERFORMANCE POLYAMIDE RESIN


Creep modulus-time 302°F (dry)



Zytel® HTN51G35HSL NC010

HIGH PERFORMANCE POLYAMIDE RESIN


Spec. enthalpy/mass-temp. (DSC)



Zytel® HTN51G35HSL NC010

HIGH PERFORMANCE POLYAMIDE RESIN


Tensile modulus-temperature (dry)



Zytel® HTN51G35HSL NC010

HIGH PERFORMANCE POLYAMIDE RESIN

Tensile modulus-temperature (cond.)



Zytel® HTN51G35HSL NC010

HIGH PERFORMANCE POLYAMIDE RESIN

Chemical Media Resistance

Acids

- ✔ Acetic Acid (5% by mass), 23°C
- ✔ Citric Acid solution (10% by mass), 23°C
- ✔ Lactic Acid (10% by mass), 23°C

Mineral oils

- ✔ SAE 10W40 multigrade motor oil, 23°C
- ✔ SAE 10W40 multigrade motor oil, 130°C
- ✔ SAE 80/90 hypoid-gear oil, 130°C
- ✔ Insulating Oil, 23°C
- ✔ Motor oil OS206 304 Ref.Eng.Oil, ISP, 135°C
- ✔ Automatic hypoid-gear oil Shell Donax TX, 135°C
- ✔ Hydraulic oil Pentosin CHF 202, 125°C

Standard Fuels

- ✔ ISO 1817 Liquid 1 - E5, 60°C
- ✔ ISO 1817 Liquid 2 - M15E4, 60°C
- ✔ ISO 1817 Liquid 3 - M3E7, 60°C
- ✔ ISO 1817 Liquid 4 - M15, 60°C
- ✔ Standard fuel without alcohol (pref. ISO 1817 Liquid C), 23°C
- ✔ Standard fuel with alcohol (pref. ISO 1817 Liquid 4), 23°C
- ✔ Diesel fuel (pref. ISO 1817 Liquid F), 23°C
- ✔ Diesel fuel (pref. ISO 1817 Liquid F), 90°C
- ✔ Diesel fuel (pref. ISO 1817 Liquid F), >90°C
- ✔ Diesel EN 590, 100°C

Other

- ✔ Ethylene Glycol (50% by mass) in water, 108°C
- ✔ Water, 23°C
- ✔ Water, 90°C
- ✔ Coolant Glysantin G48, 1:1 in water, 125°C

Symbols used:

✔ possibly resistant
Defined as: Supplier has sufficient indication that contact with chemical can be potentially accepted under the intended use conditions and expected service life. Criteria for assessment have to be indicated (e.g. surface aspect, volume change, property change).

✘ not recommended - see explanation
Defined as: Not recommended for general use. However, short-term exposure under certain restricted conditions could be acceptable (e.g. fast cleaning with thorough rinsing, spills, wiping, vapor exposure).

Revised: 2026-08-12 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colorants or other additives may cause significant variations in data values. Properties of molded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.
Copyright © 2026 Celanese or its affiliates. All rights reserved.
Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates.