FORTRON® CES 6145 LCG

Polyphenylene sulfide

FORTRON® CES 6145 LCG is a glass fiber and mineral reinforced grade with low Chlorine content. It offers excellent physical properties and good flowability for consumer electronics applications.

Product information

Resin Identification	PPS-(GF+MD)45		ISO 1043
Part Marking Code	>PPS-(GF+MD)45<		ISO 11469

Rheological properties

Molding shrinkage, parallel	0.3	%	ISO 294-4, 2577
Molding shrinkage, normal	0.6	%	ISO 294-4, 2577

Typical mechanical properties

Tensile modulus	2.32E6	psi	ISO 527-1/-2
Tensile stress at break, 5mm/min	27600	psi	ISO 527-1/-2
Tensile strain at break, 5mm/min	1.8	%	ISO 527-1/-2
Flexural modulus	2.32E6	psi	ISO 178
Flexural strength	40600	psi	ISO 178
Charpy impact strength, 23°C	4.28	ftlb/in²	ISO 179/1eU
Poisson's ratio	0.372		

Thermal properties

Melting temperature, 10°C/min	536	°F	ISO 11357-1/-3
Glass transition temperature, 10°C/min	194	°F	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	523	°F	ISO 75-1/-2

Flammability

Burning Behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.0157	in	IEC 60695-11-10

Electrical properties

Relative permittivity, 2GHz	4.1		IEC 61189-2-721
Dissipation factor, 2GHz	40	E-4	IEC 61189-2-721

Physical/Other properties

Water absorption, 2mm	0.02	%	Sim. to ISO 62
Density	0.0621	lb/in³	ISO 1183

Injection

Drying Recommended	yes	
Drying Temperature	266	°F
Drying Time, Dehumidified Dryer	2 - 4	h
Processing Moisture Content	≤0.02	%
Melt Temperature Optimum	626	°F
Min. melt temperature	590	°F
Max. melt temperature	644	°F

FORTRON® CES 6145 LCG


Polyphenylene sulfide

Max. screw tangential speed	0.2 - 0.3	m/s
Mold Temperature Optimum	302	°F
Min. mold temperature	284	°F
Max. mold temperature	320	°F
Hold pressure range	4350 - 10200	psi
Back pressure	435	psi

Characteristics

Processing	Injection Molding
Special characteristics	Flame retardant, Heat stabilized or stable to heat, Hydrolysis resistant, High Flow, Chemical resistant

Stress-strain




Revised: 2026-09-08 Source: Celanese Materials Database

FORTRON® CES 6145 LCG

Polyphenylene sulfide

Secant modulus-strain



FORTRON® CES 6145 LCG

Polyphenylene sulfide

Chemical Media Resistance

Standard Fuels

- ✔ ISO 1817 Liquid 1 - E5, 60 °C
- ✔ ISO 1817 Liquid 2 - M15E4, 60 °C
- ✔ ISO 1817 Liquid 3 - M3E7, 60 °C
- ✔ ISO 1817 Liquid 4 - M15, 60 °C
- ✔ Standard fuel without alcohol (pref. ISO 1817 Liquid C), 23 °C
- ✔ Standard fuel with alcohol (pref. ISO 1817 Liquid 4), 23 °C

Symbols used:

✔ possibly resistant
Defined as: Supplier has sufficient indication that contact with chemical can be potentially accepted under the intended use conditions and expected service life. Criteria for assessment have to be indicated (e.g. surface aspect, volume change, property change).

✘ not recommended - see explanation
Defined as: Not recommended for general use. However, short-term exposure under certain restricted conditions could be acceptable (e.g. fast cleaning with thorough rinsing, spills, wiping, vapor exposure).

Revised: 2026-09-08 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colorants or other additives may cause significant variations in data values. Properties of molded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.
Copyright © 2026 Celanese or its affiliates. All rights reserved.
Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates.