FORTRON® FX4382T1 FC

Polyphenylene sulfide

Fortron FX4382T1 FC is an impact-modified, unreinforced, extrusion/injection molding grade offering high tensile elongation. It is compliant with food contact requirement.

Product information

Resin Identification	PPS-I		ISO 1043
Part Marking Code	>PPS-I<		ISO 11469

Rheological properties

Molding shrinkage range, parallel	0.9 - 1.4	%	ISO 294-4, 2577
Molding shrinkage range, normal	0.7 - 1.4	%	ISO 294-4, 2577

Typical mechanical properties

Tensile modulus	334000	psi	ISO 527-1/-2
Tensile stress at break, 5mm/min	7250	psi	ISO 527-1/-2
Tensile strain at break, 5mm/min	25	%	ISO 527-1/-2
Flexural modulus	348000	psi	ISO 178
Compressive modulus	328000	psi	ISO 604
Compressive stress at 1% strain	3190	psi	ISO 604
Charpy impact strength, 23°C	N	ftlb/in²	ISO 179/1eU
Charpy notched impact strength, 23°C	19[OT]	ftlb/in²	ISO 179/1eA
Charpy notched impact strength, -30°C	4.76[OT]	ftlb/in²	ISO 179/1eA
Izod notched impact strength, 23°C	24.1	ftlb/in²	ISO 180/1A
Izod impact strength, 23°C	N	ftlb/in²	ISO 180/1U
Multiaxial impact, total energy, 23°C	540	in-lb	ASTM D 3763

[OT]: One time tested

Tribological properties

Coefficient of dynamic friction, against steel	0.2		ISO 8295

Thermal properties

Temperature of deflection under load, 1.8 MPa	212	°F	ISO 75-1/-2
Coefficient of linear thermal expansion (CLTE), parallel	0.33	E-4/°F	ISO 11359-1/-2
Coefficient of linear thermal expansion (CLTE), normal	0.428	E-4/°F	ISO 11359-1/-2
Thermal conductivity, flow	0.302[OT]	W/(m K)	ISO 22007-2
Thermal conductivity, through plane	0.31[OT]	W/(m K)	ISO 22007-2
Effective thermal diffusivity, flow	0[OT]	m²/s	ISO 22007-4
Effective thermal diffusivity, through plane	0[OT]	m²/s	ISO 22007-4
Specific heat capacity of melt	1440[OT]	J/(kg K)	ISO 22007-4

[OT]: One time tested

FORTRON® FX4382T1 FC

Polyphenylene sulfide

Electrical properties

Volume resistivity	5E14	Ohm.m	IEC 62631-3-1
Comparative tracking index	150		IEC 60112
Dielectric Constant, 1 GHz	3.3		ASTM D 2520 B

Physical/Other properties

Water absorption, 2mm	0.035	%	Sim. to ISO 62
Density	0.0455	lb/in^3	ISO 1183

Injection

Drying Recommended	yes	
Drying Temperature	266	°F
Drying Time, Dehumidified Dryer	2 - 4	h
Processing Moisture Content	≤0.02	%
Melt Temperature Optimum	626	°F
Min. melt temperature	590	°F
Max. melt temperature	644	°F
Max. screw tangential speed	0.2 - 0.3	m/s
Mold Temperature Optimum	248	°F
Min. mold temperature	176	°F
Max. mold temperature	320	°F
Hold pressure range	4350 - 10200	psi
Back pressure	508	psi
Ejection temperature	423	°F

Characteristics

Processing	Injection Molding, Extrusion
Special characteristics	High impact or impact modified

Additional information

Injection molding

Processing

Drying - alternate: 82°C overnight.

Processing Notes

Pre-Drying

Yes

Revised: 2026-09-08 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colorants or other additives may cause significant variations in data values. Properties of molded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.
Copyright © 2026 Celanese or its affiliates. All rights reserved.
Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates.