PPS

Torelina® A504XL

Toray Industries

Position #112 • Jinsutong Reference Catalog 2026

Resin Overview

PPS · 40% Glass, General. Sourced from public manufacturer technical data sheets.

This Grade

Manufacturer	Toray Industries
Category	PPS · 40% Glass, General
Typical Use	40% glass for general structural use

Key Properties

Density	1.65 g/cm³
Tensile Strength at Break	175 MPa
Tensile Modulus	13500 MPa
Elongation at Break	1.8%
HDT (1.8 MPa)	265 °C
Continuous Use Temperature	200 °C
Color	Natural
UL 94 Rating	V-0 @ 0.75mm

Key Features

- 40% glass fiber for stiffness
- UL 94 V-0 flame retardant
- High heat 200°C continuous
- Toray quality

Processing Conditions

Melt Temperature	310-330 °C

Mold Temperature	140-170 °C
Drying	4 h @ 150 °C in desiccant dryer
Processing Methods	Injection molding

Typical Applications

- General structural parts
- Automotive under-hood
- Industrial sensors
- High-temp IT structural

Regulatory & Compliance

- UL 94 V-0 listed
- RoHS compliant

> ⚠ All data sourced from public manufacturer catalogs.

Contact
Mr. Mo Hailong · +86 138 1603 7020 · 13816037020@139.com

© 2026 Shanghai Jinsutong Plastics Co., Ltd. · jinsutong.com/grades