PVDF

Solef® 6020

Syensqo

Position #110 · Jinsutong Reference Catalog 2026

Resin Overview

PVDF · Homopolymer, General. Sourced from public manufacturer technical data sheets.

This Grade

Manufacturer	Syensqo
Category	PVDF · Homopolymer, General
Typical Use	General purpose PVDF, chemical and electrical

Key Properties

Density	1.78 g/cm³
MVR (230°C/5 kg)	4 g/10min
Melting Point (DSC)	178 °C
Tensile Strength at Yield	52 MPa
Elongation at Break	60%
HDT (0.45 MPa)	140 °C
Tensile Modulus	2100 MPa
Volume Resistivity	>1e14 Ω·cm

Key Features

- Homopolymer PVDF for general use
- Excellent chemical resistance
- High dielectric strength
- Good for extrusion and injection

Processing Conditions

Melt Temperature	230-260 °C
Mold Temperature	N/A (extrusion)
Drying	4 h @ 100 °C in desiccant dryer
Processing Methods	Extrusion, injection molding

Typical Applications

- Chemical process components
- Wire and cable insulation
- Semiconductor wet process
- Industrial chemical handling

Regulatory & Compliance

- RoHS compliant
- REACH registered

> ⚠ All data sourced from public manufacturer catalogs.

Contact
Mr. Mo Hailong (莫海龙) — Business Manager · +86 138 1603 7020 · 13816037020@139.com
Shanghai Jinsutong Plastics Co., Ltd. · 1st Building, 5601 Yanqian Road, Fengxian District, Shanghai

© 2026 Shanghai Jinsutong Plastics Co., Ltd. · Jinsutong Reference Catalog 2026 · jinsutong.com/grades